

### Description

Sabadeck is an adhesive, 1-component, elastic, humidity-curing, MS polymer-based for bonding wooden and PVC decks.

### Field of application

Marine.

### Advantages

- long application time (open time) of approx. 60 minutes
- excellent and durable adhesion on many different surfaces
- no blistering
- hardly any shrinkage
- resistant to (sea)water and weather influences
- odourless
- free from solvents, isocyanates and silicones
- certificates: Wheelmark (164.106/1121/WCL MED0327)



### Method of use

For application and pre-treatment please read the corresponding info sheets and pre-treatment tables on [www.saba.nl](http://www.saba.nl)

### Technical data

<b>Basis</b>	MS polymer, humidity-curing
<b>Density</b> (EN 542)	approx. 1.310 kg/m <sup>3</sup>
<b>Solids content</b>	approx. 98 %
<b>Skin time</b> (23 °C, 50% RH)	approx. 15 minutes
<b>Open time</b> (23 °C, 50% RH)	approx. 60 minutes
<b>Tack free</b> (23 °C, 50% RH)	after approx. 48 hours
<b>Cure rate</b> (23 °C, 50% RH)	approx. 2 mm/24 hrs
<b>Hardness Shore A</b> (EN ISO 868)	approx. 35
<b>Volume alteration</b> (DIN 52451)	approx. 5 %
<b>Modulus at 100 %</b> (ISO 37/DIN 53504)	approx. 0,7 N/mm <sup>2</sup>
<b>Tensile strength</b> (ISO 37/DIN 53504)	approx. 2,0 N/mm <sup>2</sup>
<b>Elongation at break</b> (ISO 37/DIN 53504)	approx. 426 %
<b>Work temperature</b>	+ 5 °C and + 35 °C
<b>Storage temperature</b>	+ 5 °C and + 25 °C
<b>Temperature resistance</b>	-30 °C up to + 80 °C

### Order information

<b>Packing</b>	sausage
<b>Content</b>	600 ml (content 15 pieces)
<b>Colour</b>	black (similar to RAL 7021)
<b>Article no.</b>	100829 AAL
<b>Shelf life</b>	15 months (in unopened packing)

*Other packing and colours on request. On large packing the shelf life can be different.*

### Safety recommendations

For more information concerning safety please read the corresponding SABA safety data sheet.