FPC Corporation 355 Hollow Hill Dr. Wauconda, IL 60084 Tel: 847-487-4583 Fax: 847-487-0174

Specification Sheet S-12478-10

Type: Solids: Melt Point (R&B) Viscosity: Temp. Resistance: Color: Shelf Life: Open Time: Polyamide 100% 284° F-140° C @ 400° F 3,900 0° F - 248° F Amber Short – must be kept well-sealed 75 Seconds

Features: Polyamide. Low application viscosity. High temperature resistance. Long open time. Resistance to plasticizer migration for vinyl bonding.

Storage: Must be kept well-sealed

Application Temperature: 380°

Precautions: Do Not Mix with other adhesives Severe burns will result if contact is made in molten state.

The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. FPC disclaims all other warranties, expressed or implied, including the warranties of merchantability and fitness for a particular purpose. The buyer's sole remedy for non compliance with this warranty shall be for the replacement of the product or refund of the buyer's purchase price.