



Geco

Custom Wood Stain System

For More Information Please Visit
www.gecoatings.com

Instructions

Instrucciones



Custom Stain System

Beginners Guide:

How to Start: Use a scale or measuring cup for accurate results to measure by weight or volume. Kit includes a gram-scale & measuring cup for your convenience. Pick your desired wood stain color shade.

1. USE the diagram on the Right → to help you add the right portion of tint base. Add the **RED/YELLOW** combination, use a 50 gram total. (Remember to write down the number of grams of Tint Base Added)
2. NEXT: Add the Black Tint Base in small portions 1-5 grams. Note: You can always add more later. Mix Tint Base well with a stirring stick until all colors have fully dissolved. (Remember to write down the number of grams of Tint Base Added)
3. TEST your color on a piece of sanded wood by applying stain with cloth or brush, then wipe stain with cloth to obtain smooth even staining. Let dry for 15 minutes, before coating with a **Solvent-Based Lacquer**.
4. If you want your Custom Stain Color **DARKER**: Add more Black Tint Base in small 1-5 gram increments. If you want your Custom Stain **LIGHTER**: Add Lightener in 20-40 gram portions. (Remember to write down the number of grams Added)

Guia para Estudiantes:

Cómo empezar: Usa una báscula o una taza de medición para obtener resultados exactos, mide por peso o volumen. El kit incluye una báscula en gramos y una taza de medición para tu comodidad. Elige tu barniz para madera del color deseado.

1. Usa el diagrama de la derecha que te ayudará a agregar la cantidad correcta de la base de color. Agrega la combinación **ROJO/AMARILLO**, usa un total de 50 gramos. (Recuerda escribir debajo el número de gramos de la base de color agregados)
2. SIGUIENTE: Agrega la base de color negro en pequeñas porciones de 1 a 5 gramos. Nota: Siempre podrás agregar más después. Mezcla la base de color bien con un palo de agitación hasta que los colores estén completamente disueltos. (Recuerda escribir debajo el número de gramos de la base de color agregados)
3. PRUEBA tu color en una pieza de madera lijada, aplicando el barniz con un pedazo de tela o brocha, después limpia el barniz con una tela para obtener un resultado uniforme y sin manchas. Deja secar por 15 minutos antes de cubrir con el **lácquer a base de solvente**.
4. Si tu deseas tu color de barniz **MAS OSCURO**: Agrega más base de color negro en pequeños incrementos de 1 a 5 gramos. Y si lo deseas **MAS CLARO**: Agrega reductor en porciones de 10 a 40 gramos. (Recuerda escribir debajo el número de gramos agregados)

Color Shades



ADD Black Tint Base: 2-5 grams

TEST the COLOR

LIGHTEN

DARKEN

ADD Lightener: 10-40 grams

ADD Black Tint Base: 2-5 grams

Cloudy Orange

Inter-blend with RED/YELLOW or substitute for RED/YELLOW giving a more earthy, hazy looking stain.

	RED	YELLOW	BLACK	Lightner	Orange	Total
Formula A	(a)	(b)	(c)		(e)	(X)
Formula B						

*****Your Formula:** Add All the numbers of grams used- a,b,c,d,e,f. Then, take that number (TOTAL x) and Divide each Color by the TOTAL: a/x, b/x, c/x, e/x.

To make 1 Quart of Your Color **multiply** the fraction of each product by 900 grams. FOR EXAMPLE: a/x **X** 900 = the amount RED needed, b/x **X** 900 = YELLOW etc... All the ingredients should add up to a 900 gram Formula. Gallon **X** by 3600 grams & 5 gallons by **X**18,000 grams

** Stain Colors will appear dull, until topcoat is applied to intensify the true color