

## ECOFIX



5L 1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

### Ciranova North-America

1255 22nd Street  
San Francisco, CA 94107  
tel. 415.282.2529 fax 415.477.2106  
info@ciranova-na.com

### PRODUCT DESCRIPTION

Water based impregnation oil for parquet and wooden furniture. Only for interior use. In partucularly for interior where a natural finish is needed such as parquet, veneer and other wooden objects

### TECHNICAL DATA

VISCOSITY	+/- 20 sec. (Din 4mm/68°F)
SOLID CONTENTS	+/- 25 % by weight
DENSITY	+/- 1,00 kg/lt.
GLOSS	matt
NMP FREE	
CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010	

### PREPARATION

Surface: Solid wood, ingeneerd wood. Sand the surface with grain 100-150 and afterwards remove sanding dust.

### USER TIPS

Use the ECOFIX Ciranova as a sealer and topcoat. Mix the product well before use. After mixing or stirring the product, the product have to rest for 15 minutes before use. Application is done by a brush or roller.

Apply the first coat wet in wet to avoid overlapping. When the first layer is dry, apply the second layer as the first layer. When the second layer is dry, sand with grain 150-180, remove sand dust and apply the third layer.



### DRYING TIMES

Dust free: 20 to 30 minutes  
Sandable: 2 to 4 hours  
Chargeable after 24 hours

The drying is strongly depending on the applied quantity, the temperature, air humidity and the ventilation of the room. Through a higher temperature and a good ventilation, drying time is limited.



### APPLYING QUANTITY

107-129 sq ft/l.

### AFTERTREATMENT

- Use Hard floor fresh Ciranova for regular maintenance.
- Ecofix Woodlook can also be finished with a lacquer out of the Ciranova Aquafix gamma.

### PRODUCT INFORMATION

12 months in well-closed and original packing.  
Warehousing at + 41°F – 104°F: not frost-durable.

### SPECIAL QUALITIES

Use only stainless material. After use, since the material directly with water. This product cannot be poured into sewerage. If a stain on the wood is needed, only use AQUACOLOR Ciranova. Be aware of discoloration or detachment because of wood compounds like resins or tanin.