



CenoBar Properties

Series	Grade	BaS04	Median Particle size (µm)	True Density (g/cm ³)	Whiteness	Moisture Content	pH Value	Oil Absorption
	CENOBAR 10	96.5-98%	2 +/- 0.2	4.3 +/-0.5	93-95	0.3%	7 +/- 2	11-15
	CENOBAR 20	96.5-98%	4 +/- 0.2	4.3 +/-0.5	93-95	0.3%	8 +/- 2	11-15
	CENOBAR 25	96.5-98%	6.5 +/- 0.5	4.3 +/-0.5	93-95	0.3%	8 +/- 3	10-14
	CENOBAR 45	96.5-98%	9 +/- 1.0	4.3 +/-0.5	93-95	0.3%	8 +/- 4	9-13
Blanc Fixe	CENOBAR BLANC FIXE	>98.5%	1.0 +/- 0.25	n/a	96-99	n/a	~9	13-20

Above are Cenostar's standard grades of barytes displaying typical properties. CenoStar can provide alternative grades with altered properties of certain spec if requested. CenoStar sources directly from one mine which allows us to acquire consistency in our color and other properties.

The Information herein is accurate to the best of CenoStar's knowledge. Before using, user should test properties and user assumes the risk and liability in connection therewith.