

## Technical Tip

# Mill Glaze

Although there is some controversy regarding its cause, the most commonly held theory about the formation of mill glaze is that it is created on logs, siding and trim by heat and mechanical compression generated during a high speed milling process. The combination of compressed wood fibers and high temperatures that melt the sugars and other water-soluble extractives present in the wood end up forming a surface glaze. If not removed, this glaze can interfere with the adhesion of both water and oil-based coatings since the wood's cellular surface is not in direct contact with the coating.

The best way to remove mill glaze from exterior wood surfaces is by using Wood ReNew and pressure washing. We highly recommend this procedure whenever a finish is going to be applied to new exterior siding. For interior surfaces a light sanding followed by a light washing with Log Wash and wiping the wall with warm water will help swell and decompress the wood fibers and dissolve the glaze, thus assuring the adhesion of our finishes to the surface of the wood.



**Mill Glaze**