

## Technical Tip

# Mixing Advance Satin

Although there is not much difference in the formulation between Advance Satin and Advance Gloss, Advance Satin contains a flattening agent that can settle to the bottom of the container over time. It's important to mix ALL of our finishes before and during use including Advance. Since it does contain a flattening agent, be sure to shake or mix Advance Satin until none of the flattening agent remains at the bottom of the pail or gallon container. During use the container should be mixed or shaken again every 20 to 30 minutes to assure a uniform dispersion. This will avoid areas of a wall or home looking “flatter” than others.

If inadequately mixed Advance Satin is applied to a wall, the only way to remove the white residue is to strip the entire finish off and start over again.



**Inadequately mixed Advance Satin  
applied to home.**