



VK122HM Double Sided Tape - Tissue

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Adhesive type: Pressure-sensitive hotmelt rubber/resin

Thickness, adhesive + carrier

0.080

mm

Release liner thickness

0.055

mm

180 degree peel adhesion: Open side
 Closed side

800

N/m

800

N/m

Polyester loop tack: Open side
 Closed side

850

N/m

850

N/m

Liner release

10

N/m

Tensile strength

1200

N/m

Elongation at break

10

%

Service temperature

-10 to +60

Deg. C.

Recommended application temperature

+5 to +60

Deg. C.

Shear adhesion, 1Kg @ 23 deg. C.

Greater than 100

Hours

Shelf life

12

Months

Test Methods: BS 7116

.THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY
ALL DATA IS BASED UPON AVERAGE VALUES THE PURCHASER SHALL BE RESPONSIBLE FOR
.DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES