Unit 1, Coronation Business Park, Hard Ings Road, Keighley, West Yorkshire, BD21 3ND

VK3054 - Double Sided Tape - Polyester

TECHNICAL DETAILS		TYPICAL VALUE	UNITS
Thickness, adhesive + carrier Release liner thickness		0.070 0.075	mm mm
180 degree peel adhesion:	Open side Closed side	750 750	N/m N/m
Polyester loop tack:	Open side Closed side	850 850	N/m N/m
Liner release		10	N/m
Tensile strength		4600	N/m
Elongation at break		12	%
Service temperature		-20 to +120	Deg. C.
Recommended application temperature		+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.		20	Hours
Shelf life		12	Months
Test Methods: BS 7116			

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY
ALL DATA IS BASED UPON AVERAGE VALUES THE PURCHASER SHALL BE RESPONSIBLE FOR
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES