Unit 1, Coronation Business Park, Hard Ings Road, Keighley, West Yorkshire, BD21 3ND

## VKATG2325

Product datasheet Issue No 4

Issued Nov 2004

## RA 2320/2325 EURATRANS REINFORCED ACRYLIC TRANSFER TAPE

2320 on std. 76mm cores, 2325 on 25mm dispenser cores

TECHNICAL DETAILS		TYPICAL VALUE	<u>UNITS</u>
Thickness, adhesive + carrier Release liner thickness		0.060 0.055	mm mm
180 degree peel adhesion:	Open side Closed side	700 700	N/m N/m
Polyester loop tack:	Open side Closed side	500 500	N/m N/m
Liner release		10	N/m
Service temperature		-10 to +100	Deg. C.
pH of water extract		7.0 - 7.5 *	
Recommended application temperature		+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.		30	Hours
Shelf life		12	Months

Test Methods: BS 7116 \*Test Method BS EN 60454-2

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR
DETEMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.