


KLUANE

ICONIC COLLECTION

Northern
WIDE PLANK



SPECIFICATIONS

MANUFACTURED:	MADE IN CANADA
WOOD ORIGIN:	NORTH EASTERN/CENTRAL USA
WOOD SPECIES:	WHITE OAK
TYPE:	ENGINEERED
GRADE:	AVAILABLE IN CHARACTER OR SELECT
SHADE:	DARK
SURFACE:	SANDED
EDGES:	MICROBEVELLED (PLANK - LONG SIDES ONLY)
THICKNESS:	20 MM (3/4") WITH 6 MM WEAR LAYER *TOP LAYER THICKNESS IS MEASURED BEFORE THE FINISHING PROCESS.

HIGH ABOVE THE POPLARS AND SPRUCE, MOUNT LOGAN STANDS LIKE A SENTRY IN KLUANE NATIONAL PARK AND RESERVE. KLUANE WHITE OAK PLANKS ECHO THE MAJESTY AND UNWAVERING PRESENCE OF THIS MASSIVE MOUNTAIN. STAINED WITH A RICH, NUTTY TONE, THESE SLOW-GROWTH HARDWOODS MAKE A STATEMENT, WITH ROOTS FROM THE COLONIAL TO THE TRADITIONAL STYLE.

CONSTRUCTION:	PURECRAFT 3-LAYER OR WBP BALTIC BIRCH PLYWOOD
FINISH:	HARDWAX OIL (UV CURED)
PLANK WIDTHS:	178 MM / 229 MM / 280 MM (7" / 9" / 11")
PLANK LENGTHS:	914 MM - 3581 MM (36" - 141")

HERRINGBONE DIMENSIONS:	4" X 20" (101.6 MM X 508 MM)
CHEVRON DIMENSIONS:	4" X 16" (101.6 MM X 406.4 MM)
COLOUR VARIATION:	V1 - SLIGHT VARIATION
CERTIFICATIONS:	

CLEANING AND CARE

Northern Wide Plank requires a relative humidity range of minimum 30%, maximum 65%, and a temperature range between 15°C (60°F) to 24°C (75°F). Refer to NWP Cleaning & Care for Hardwax Oil finished wood floors for more info.



Declare.

FSC® AVAILABLE UPON REQUEST

TECHNICAL PERFORMANCE

ESSENTIAL CHARACTERISTICS

Reaction to fire
Emission of Formaldehyde
Janka Hardness Rating
Post Consumer Recycled Content %

PERFORMANCE

ASTM E 648-17 Class II
E1 / CARB 2 compliant
1,360 lbf (6,000 N)
NA

INSTALLATION

TYPE	RECOMMENDATION
Full Glue Down	YES - RECOMMENDED
Nail Down	YES - WITH GLUE ASSIST
Floating	NOT RECOMMENDED
Over Underfloor Heating	YES - REFER TO NWP RADIANT HEAT GUIDE

APPLICATIONS: Floors, Walls and Ceilings. Stair Treads, Nosing, and Vents are also Available.

5930 LLOYDTOWN-AURORA ROAD, SCHOMBERG ON L0G 1T0 CANADA
NORTHERNWIDEPLANK.CA 877/763/6169

Date: Mar 7, 2024