

## 1/8" (.115") Thick Non-Woven Geotextile Fabric

Series: Non-Woven Geotextile Fabric

Recommended Applications: Drainage, Erosion Control

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
Weight	ASTM D5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	10.0 (339)
Thickness	ASTM D5199	mils (mm)	115 (2.9)
Grab Tensile Strength	ASTM D4632	lbs (N)	270 (1202)
Grab Tensile Elongation	ASTM D4632	%	50
Trapezoid Tear Strength	ASTM D4533	lbs (N)	105 (467)
CBR Puncture Strength	ASTM D6241	lbs (N)	725 (3226)
			<b>Minimum Roll Value</b>
Permittivity	ASTM D4491	sec <sup>-1</sup>	1.2
Permeability	ASTM D4491	cm/sec	0.32
Flow Rate	ASTM D4491	gal/min/ft <sup>2</sup> (l/min/m <sup>2</sup> )	85 (3463)
			<b>Maximum Opening Size</b>
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	100 (0.15)
			<b>Minimum Test Value</b>
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	80

Physical Properties	Unit	Roll Size
Roll Dimensions (width x length)	ft (m)	15 x 300 (4.5 x 91)
Roll Area	yd <sup>2</sup> (m <sup>2</sup> )	500 (418)

To the best of our knowledge, the information contained herein is accurate. However, Pro Fabric Supply cannot anticipate all conditions under which the above product information and the products which we distribute or the products of other distributors or manufacturers in combination with the products which we offer, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of the products we distribute either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.

Please note: Pro Fabric Supply is a distributor of geotextile fabric, not the manufacturer. We source material from a number of different United States based geotextile manufacturers.