

## Woven Geotextile Fabric

Series: Stabilization - Heavy-Duty Grade A

Recommended Applications: Stabilization below gravel roadways, driveways and parking areas

Roadway Design and Performance Properties	Guidance Document / Test Method	Unit	Design / Calibration Value	
Base Course $M_R$ Improvement Factor <sup>1</sup>	AASHTO R50-09	---	1.40	
Subgrade $M_R$ Improvement / Increase <sup>2</sup>	AASHTO R50-09	lb/in <sup>2</sup> (MPa)	9,000 (62.0)	
Cyclic Tensile Modulus: $J_{cyclic}$ <sup>3</sup>	ASTM D7556	kip/ft (kN/m)	MD	CD
			60 (876)	160 (2,336)
Resilient Interface Shear Stiffness: $G_i$ <sup>3</sup>	ASTM D7499	kip/in <sup>2</sup> (MPa)	329 (2,268)	
Traffic Benefit Ratio: TBR <sup>4,5,6</sup>	AASHTO R50-09	---	9.0 / 13.1 / 39.0	
Interaction Coefficient: $C_i$ <sup>7</sup>	ASTM D6706	---	0.90	
Pore Pressure Dissipation Ratio <sup>4</sup>	Measured	---	2.0	
Typical Dynamic Filtration Pore Size $O_{95}$ / $O_{50}$ <sup>8</sup>	ASTM D6767	microns	337 / 192	
Maximum Percent Open Area: MPOA <sup>9</sup>	ASTM D6767	Percent	7.3	
Tensile Strength @ 2% Strain (MARV)	ASTM D4595	lb/ft (kN/m)	480 (7.0)	1,800 (26.3)
Tensile Strength @ 5% Strain (MARV)	ASTM D4595	lb/ft (kN/m)	1,440 (21.0)	4,380 (63.9)

Index Properties	Test Method	Unit	Roll Value	
Apparent Opening Size, AOS (Maximum Roll Value)	ASTM D4751	U.S Sieve (mm)	40 (0.425)	
Hydraulic Flow Rate (MARV)	ASTM D4491	gal/min/ft <sup>2</sup> (l/min/m <sup>2</sup> )	75 (3,056)	
Permittivity (MARV)	ASTM D4491	sec <sup>-1</sup>	1.0	
UV Resistance (at 500 hours exposure)	ASTM D4355	% strength retained	90	

To the best of our knowledge, the information contained herein is accurate. However, Pro Fabric Supply cannot anticipate all conditions under which the above product information and the products which we distribute or the products of other distributors or manufacturers in combination with the products which we offer, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of the products we distribute either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.

Please note: Pro Fabric Supply is a distributor of geotextile fabric, not the manufacturer. We source material from a number of different United States based geotextile manufacturers.