

## Woven Geotextile Fabric

Series: Stabilization - Intermediate Grade C

Recommended Applications: Stabilization below gravel roadways, driveways and parking areas

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D4595	lbs/ft (kN/m)	3600 (52.5)	3240 (47.3)
Tensile Strength (at 5% strain)	ASTM D4595	lbs/ft (kN/m)	1500 (21.9)	1560 (22.8)
			Minimum Roll Value	
Flow Rate	ASTM D4491	gal/min/ft <sup>2</sup> (l/min/m <sup>2</sup> )	40 (1630)	
Permittivity	ASTM D4491	sec <sup>-1</sup>	0.9	
			Maximum Opening Size	
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	40 (0.425)	
			Typical Test Value	
Pore Size 0 <sub>95</sub> <sup>1</sup>	ASTM D6767	microns	292	
Pore Size 0 <sub>50</sub> <sup>1</sup>	ASTM D6767	microns	158	
			Minimum Test Value	
Factory Sewn Seam	ASTM D4884	lbs/ft (kN/m)	2400 (35.0)	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	80	

<sup>1</sup> Based on Third Party Testing

To the best of our knowledge, the information contained herein is accurate. However, Pro Fabric Supply cannot anticipate all conditions under which the above product information and the products which we distribute or the products of other distributors or manufacturers in combination with the products which we offer, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of the products we distribute either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.

Please note: Pro Fabric Supply is a distributor of geotextile fabric, not the manufacturer. We source material from a number of different United States based geotextile manufacturers.