

NANODIAMOND COATING



DIAMOND BODY 36

Caramel Gloss and Slick Feel

Diamond Body 36 offers many characteristics of professional vehicle coatings yet doesn't require professional training. With proper preparation, Diamond Body 36 will yield up to 36 months of hardened, hydrophobic protection.

APPLICATION INSTRUCTIONS

PRECAUTIONS

Apply in temperatures between 10-30C, 50-90F.

Apply in a closed, well ventilated, indoor area with air humidity not exceeding 70%.

Use fresh suede & microfiber towels for application of additional layers (do not use previously used towels).

APPLICATION TIPS

Hand polish/buff after application (do not use machine tool).
Apply to headlights, rubber and metal trim elements.

If application in hot climate (over 30C/90F), lower flashing time to 3-5 min. Use an additional light source to control your work when polishing treated surfaces.

WHAT YOU'LL NEED

- 2 Microfiber Towels
- Microfiber Applicator
- Diamond Body Prep
- Protective Gloves

BEFORE APPLYING - CLEANING AND DECONTAMINATION

Be sure to apply Diamond Body Prep or isopropyl alcohol to ensure there are no remnants of polishes or waxes.

Wipe down with a microfiber towel to remove any residues left from the cleaning product used. Allow the surface to dry completely before application of Diamond Body 36.

APPLICATION - ESTIMATED APPLICATION TIME: 90 min | 2 LAYERS



Shake well for 15 seconds and then apply 8-10 drops of Diamond Body 36 on a microfiber applicator. Use a clean side of the applicator for each new layer.



Using even cross hatch movements, apply Diamond Body 36 to 3-4 elements of the car body



Wait 15 min and begin to polish the treated surfaces with a clean microfiber towel to level and evenly spread the coating. Repeat procedure till all elements are coated.



If applying 2 layers of Diamond Body 36 (recommended), follow previous instructions, taking note to wait 60 min before application of the second layer.

60 min after application the car is ready for exploitation.