





## Clear Regular Body PVC Cement

Christy's **CLEAR** Regular Body PVC Cement is a professional grade, regular body, fast set, high strength PVC solvent cement. For use in plumbing, pool and spa, electrical conduit or irrigation applications.

- Professional grade, high strength PVC cement specially formulated to bond small diameter pipe and fittings
- Clear formulation for clean joints in exposed installations
- For PVC pipe sizes thru 4" (100mm). Not for schedule 80 applications
- For PVC pipe and fitting applications; potable water, pressure, non-pressure, conduit, drain, duct, DWV and sewer
- Low VOC

PRODUCT SPECIFICATIONS	
Pipe Type	PVC, Schedule 40 Only
Cement Uses:	For PVC pipe and fitting applications; potable water, pressure, non-pressure, conduit, drain, DWV, and sewer
Maximum Diameter	For PVC pipe sizes thru 4" (100mm). Not for Schedule 80
Color	Clear
Relative Set Time	Fast Set
Body	Regular Body
Performance Specification	ASTM D-2564, NSF/ANSI 14, NSF/ANSI 61, NSF/ANSI 372
Brookfield Viscosity	Minimum 90 cP @73°F +/- 2°F 23°C +/- 1°C
Specific Gravity	Typical 0.907 +/- 0.01
Industry Listing	 U.P. Code PW-DWV-SW
Max VOC Emissions	510 g/l per SCAQMD Rule 1168 Method 316A 
Shelf Life	3 Years
LEED Compliant	Low VOC formulation can earn credit toward the U.S. Green Building Council's LEED certification for green buildings. 

CASE PACK CONFIGURATIONS			
Item #	Can Size	Cans/Cs	Can UPC
RH-RCLV-QP-24	¼ Pint, 4 oz (118 ml)	24	044752335584
RH-RCLV-HP-24	½ Pint, 8 oz (237 ml)	24	044752335560
RH-RCLV-PT-12	Pint, 16 oz (473 ml)	12	044752335577
RH-RCLV-QT-12	Quart, 32 oz (946 ml)	12	044752335591
RH-RCLV-GL-6	Gallon, 128 oz (3.785 l)	6	044752335553

**SPECIAL CONSIDERATIONS:** Consult the SDS for health and safety specifics. Always use in a well-ventilated environment. Wear safety glasses and gloves at all times. **DO NOT USE** a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with PVC and CPVC solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system - this solution will be non-volatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

T. Christy Enterprises, Inc.



655 E. Ball Rd. • Anaheim, CA 92805

Tel: (714) 507-3300 • Fax: (714) 507-3310

www.TChristy.com • 800-BLU-GLUE

**THIS PRODUCT IS NOT FOR USE IN A SYSTEM USING OR BEING TESTED WITH COMPRESSED AIR OR GASSES.**