





Features

Safety Sealed Packaging (S-XXL) 100 Gloves/Box (S-L) , 90 Gloves/Box (XL-XXL)

- Textured finish
- Natural Color
- 9 mil thickness for better protection against punctures, rips and certain chemicals
- Excellent tactile sensitivity and comfortable fit
- Superior strength and durability
- Low modulus compound for maximum softness and comfort
- Dated Lot Codes for quality a ssurance and traceability

SureGrip[®] Plus Manufacturing Standards

*Brand new state-of-the-art manufacturing plant with computercontrolled market leading technology

| Defect | Inspection Level | AQL |
|---|---------------------|-----|
| Pinholes (FDA 1000 ml watertight test) | G1 | 1.5 |
| Visual Defects (Major) | G1 | 2.5 |
| Visual Defects (Minor) | G1 | 4.0 |
| Dimensions | S-2 | 4.0 |

SureGrip® Plus Textured Powder-Free Latex Exam Gloves

| Size | Reorder# |
|----------|----------|
| Small | 039-6 |
| Medium | 039-7 |
| Large | 039-8 |
| X-Large | 039-9 |
| 2X-Large | 039-0 |

All specifications are subject to change without notice.

| Specification (mm) | | | | | |
|--------------------|-----------------|---------------|-------------------|-------------------|---------------------|
| Size | Glove Length | Palm Width | Cuff Thickness | Palm Thickness | Finger Thickness |
| Small | 240 | 75 | 0.13 ± 0.01 | 0.16 ± 0.01 | 0.23 ± 0.01 |
| Medium | 240 | 85 | 0.13 ± 0.01 | 0.16 ± 0.01 | 0.23 ± 0.01 |
| Large | 240 | 95 | 0.13 ± 0.01 | 0.16 ± 0.01 | 0.23 ± 0.01 |
| X-Large | 240 | 105 | 0.13 ± 0.01 | 0.16 ± 0.01 | 0.23 ± 0.01 |
| 2X-Large | 240 | 115 | 0.13 ± 0.01 | 0.16 ± 0.01 | 0.23±0.01 |

Quality Standards

Testing Methods

- Meets or exceeds the following standards: ASTM3578, D3578, D5151, D3767, D412, D6124, EN 455 (1&2), AS 40 (Australia), FDA, CE
- Quality sampled in accordance with MIL STD 105D
- ISO 9001 Certified Manufacturing
- Meets the Viral Penetration Test (ASTM F1671)

Physical Properties

| Property | ASTM Minimum | SureGrip [®] Plus |
|----------------|--------------|----------------------------|
| | Before Aging | Before Aging |
| Tensile (MPa) | 18 | 21 |
| Elongation (%) | 650 | 750 |
| | | |
| | AfterAging | After Aging |
| Tensile (MPa) | 14 | 18 |
| Elongation (%) | 500 | 600 |
| | | |