

MasterEmaco N 5100

Cementitious polymer modified thin layer fairing mortar

Material Description

MasterEmaco N 5100 is a concrete-grey, ready-to-use mortar based on hydraulic binders, high grade quartz sands and modified with synthetic polymers. It contains no chlorides or other salts that might cause corrosion or blooming.

Areas of Application

MasterEmaco N 5100 is especially suitable for levelling uneven surfaces, filling honeycombs and pin holes. It can be used as a topping (render) of up to 3mm thick to face up masonry.

MasterEmaco N 5100 is ideal for thin resurfacing of damaged concrete surfaces, such as in rain damaged slabs and for use in non-moving crack repairs.

Characteristics and Benefits

- Multi-purpose – allows thin layer patching and feather edging
- Strong adhesion – bonds permanently to existing concrete
- Thixotropic material - quick and easy to apply by trowel vertically and overhead
- Durable - weatherproof and shrinkage compensated
- Fast return to service - high early strength and excellent bonding

Properties

Compressive strength 28 Days	40 MPa
Flexural strength 28 days	7.0 MPa
E-Modulus 28 days	12.0 GPa
Bond (to substrate)	> 2.5 MPa
Co-efficient of thermal expansion (ASTM C531)	13×10^{-6} m/m/°C
Supply form	Powder
Water added per bag (20kg)	up to 3.5 litres
Colour	Grey
Density (mixed)	2.0 kg/litre
Storage temperature	5-35°C
Application temperature	not below 7°C

Working time at 20°C	50 minutes
At 30°C	25 minutes
AS 4020 water potability	Passed
VOC Content: 7g/L	
Test method: SCAQMD: 304-91	

Application

Surface Preparation

Surfaces to which **MasterEmaco N 5100** mixtures are to be applied, should be clean, sound and free of dust and loose particles.

Cement laitance, oil, grease, mould release oil or curing compound must be removed from concrete surfaces by using wire brush, bush hammer, scabber, gritblasting or other means. Spalled or deteriorated concrete should be repaired with a suitable MasterEmaco mortar such as **MasterEmaco N 5200CI** or **S 5300CI** prior to the application of **MasterEmaco N 5100**.

All absorbent surfaces to be treated with **MasterEmaco N 5100** mortars must be thoroughly dampened to saturate all pores. During application, the temperature of the substrate should not be below 7°C.

To avoid too high surface temperatures it is advised to shade areas for the period of application.

Mixing

Pour water approximately 3.5 litres of water into a suitable pail and add **MasterEmaco N 5100** powder whilst mixing continuously until a homogeneous, lump-free mix is obtained. Adjust water to give a suitable consistency dependent on ambient temperature and relative humidity. In hot and dry climates, slightly higher amounts of water may be necessary, the contrary in cold and humid climates.

Use a low speed stirrer (300-600) with an upward mixing helical mixing paddle to entrap as little air as possible.

Do not mix **MasterEmaco N 5100** with additional cement, sand or aggregate.

Priming is not required.

MasterEmaco N 5100

Cementitious polymer modified thin layer fairing mortar

Method of Use

Apply the well-mixed **MasterEmaco N 5100** without delay to the prepared damp surface with a spatula or trowel; thin layers may be applied with a brush. A minimum temperature of 7°C is essential. Layers up to a maximum of 3mm per coating can be applied.

Depending on the finish desired, treat the surface of **MasterEmaco N 5100** after it starts to set with a foam or sponge trowel.

Estimating Data

A 20kg bag of **MasterEmaco N 5100** mixed with 3 – 3.5 litres of water yields 11 litres (0.011m³), therefore material requirement is 5.5kg/m² @ 3mm thickness.

MasterEmaco N 5100				
L	Thickness in mm /m ²	m ³	bags /m ³	m ² /mm thickness
11	11mm	(0.011)	91	11 m ²

Packaging

MasterEmaco N 5100 is available in 20kg bags.

Storage & Shelf Life

MasterEmaco N 5100 has a shelf life of 12 months. Store inside out of direct sunlight, clear of the ground on pallets.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

Disclaimer

MasterEmaco-N5100-ANZ-VI I-0523

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
11 Stanton Road
Seven Hills NSW 2147

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
Albany, Auckland
New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
0800 001 607 within New Zealand

