

MasterProtect 816CP

A free-flowing fast setting grout, for embedding discrete anodes

Material Description

MasterProtect 816CP is a cementitious grout/mortar that is specifically formulated for embedding discrete anodes used in impressed current cathodic protection installations of reinforced concrete. **MasterProtect 816CP** is especially developed for optimum life expectancy of these CP installations. **MasterProtect 816CP** is a blend of hydraulic cements, selected silica, modifying agents and special additives for pH buffering. When mixed with potable water, **MasterProtect 816CP** forms a long open timed grout with extraordinary flow characteristics.

Areas of Application

Embedding discrete anodes used in impressed current cathodic protection installations.

Characteristics and Benefits

- Improved acid resistance compared to normal grouts against the chemicals created at the anode surface – long life of the anode encasement.
- Low resistivity – enhances current flow through anode.
- Expands during setting - guarantees good filling of the hole and embedding of the anode.
- Long open time – more than 1 hour of working time.

Properties

Supply form	Powder
Grain size (max)	0.4mm
Water added per bag (20kg)	3 – 3.6 litres
Colour	Grey
Density (mixed)	~2.0kg/L
Compressive Strength (@3.6 litres/20kg bag)	
- 1 day	18 MPa
- 7 days	41 MPa
- 28 days	50 MPa

Flexural strength 7 days	7 MPa
Electrical Resistivity (Wenner 4 probe method)	
- 7 days	~2700 Ω.cm
- 28 days	~5300 Ω.cm
- 56 days	~8700 Ω.cm
- 90 days	~12000 Ω.cm

Application

Substrate Preparation

Loose particles in the holes should be removed. Slightly dampen the substrate if possible and remove free standing water.

Mixing

Pot life ± 1 hour
Final set ± 2.5 hours

Approximately 3-3.6 litres of water per 20kg powder is necessary in order to obtain the required flowing consistency. To control set time it is advised to use warm water in cold environments and cold water in warm conditions.

MasterProtect 816CP can be mixed mechanically. Gradually blend the powder into clean water. Mix until lump free consistency is obtained. Do not overmix.

Application

Do not apply **MasterProtect 816CP** if ambient temperature is below 5°C or expected to fall below 5°C within 4 hours.

All holes can simply be filled with the material. To assist complete filling of those holes, it can be necessary to move the anodes up and down, in order to release any entrapped air.

Estimating Data

A 20kg bag of **MasterProtect 816CP** mixed with 3 litres of water yields 10.5 litres.



MasterProtect 816CP

A free-flowing fast setting grout, for embedding discrete anodes

Curing

MasterProtect 816CP is self-curing. In hot, dry or windy environments it can be necessary to cover the material with some wet cloths after the initial set.

Cleaning

MasterProtect 816CP is a cementitious product. Tools should be cleaned with water before the material hardens.

Packaging

MasterProtect 816CP is available in 20kg moisture resistant paper bags.

Storage & Shelf Life

MasterProtect 816CP is can be stored in tightly sealed original bags for 12 months if kept dry and at moderate temperature.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

Disclaimer

MasterProtect-816CP-ANZ-V6-0723

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 11 Stanton Road
 Seven Hills NSW 2147

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Freecall: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

