

MasterFinish 222

General purpose form release agent

Material Description

MasterFinish 222 is a low viscosity, chemical release agent for all types of concrete formwork. MasterFinish 222 reacts with the alkalis and water at the interface of the concrete and formwork to produce a thin film of lime soap which breaks the bond enabling the formwork to be readily stripped.

Areas of Application

- Use on all types of formwork to enable clean stripping of forms and provide excellent architectural finishes.
- Use in all concrete construction whether "in situ", precast or prestressed.
- Application to wheelbarrows, trowels, buckets and other construction tools to facilitate cleaning and provide temporary protection against rusting.
- Application to metal window and door frames to prevent adhesion of cement and mortar splashes during construction.

Characteristics and Benefits

- No discolouration or blotchiness, provides stain-free, "off-form" architectural concrete finishes.
- High coverage rate MasterFinish 222 is economical to use.
- Suitable for use with normal, off-white and coloured concrete.
- Leaves no residue on concrete finish.
- Excellent "off-form" finish - produces a clear reproduction of formwork texture and sharp concrete features.
- Reduces the incidence of air pockets and tendency of surface spalling at corners.
- Will not impair the bond of subsequent applications of paint, render or tiles.
- Preserves and waterproofs timber forms and inhibits rusting of steel forms in use or storage.
- Protects aluminium windows and door frames from plaster and mortar splashes.
- Easy to use, requires no mixing on site.

Application

Surface Preparation

Remove any excessive film of old form oil, dirt, dust or other contaminants. Surfaces should be clean with no free moisture present.

Application

MasterFinish 222 can be used direct from the container. Apply thinly and evenly using a low pressure spray, sponge mop, broom, roller or brush. Remove any puddles or excess accumulation, or the concrete surface may be left powdery.

MasterFinish 222 should be applied before placing reinforcing steel. Any accidental spillage on steel reinforcement should be removed using a clean rag dampened with turpentine or xylol. Concrete may be placed soon after the coating has been applied or several days later. Formwork may be stripped as required.

Re-coat forms prior to each use.

Estimating Data

Coverage will vary depending on the type of formwork, as a guide:

Type of Formwork	m ² per litre
Non-absorbent	30 – 60
Smooth plywood or dense grained timber	20 – 40
Porous or rough sawn timber	16 - 24

Packaging

MasterFinish 222 is available in 20 litre plastic pails and 200 litre drums.

Storage & Shelf Life

MasterFinish 222 can be stored for 24 months in unopened, original containers. Do not allow to freeze, if frozen discard.



MasterFinish 222

General purpose form release agent

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

Disclaimer

MasterFinish-222-ANZ-V7-0523

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 11 Stanton Road
 Seven Hills NSW 2147

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Phone: +64 9 414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

