


	<b>VITAL TECHNICAL SDN. BHD.</b>	  
	Technical Data Sheet	
	<b>VT-130 / VT-134 Clear Sealant</b>	

Issuance date: 31/03/08

Revision date: 30/09/20

Revision No.: 20-02

### Product Specifications:

Curing system	: Acetoxo
Appearance	: Paste
Color	: Translucent
Odor	: Vinegar-like
Specific gravity:	: 1.06
Curing time (t=5mm)	: 2 days
Hardness JIS K 6249	: Shore A ≥18
Tensile at break JIS K 6249	: ≥1.2 MPa
Elongation at break JIS K 6249	: ≥300%
Application temperature	: -20 °C to 50 °C
Service temperature	: Up to 150 °C
Shelf life	: 24 months
Features	: Permanently flexible : Durable : Indoor and outdoor use

#### Packaging

Product Code	Content	Inner Box	Carton
VT-130	75 g tube card	12	144
VT-134	32 g tube card	12	144

(Scan to learn how to use)



VT-130

VT-134

Visit product page:

<https://vitaltechnical.com/product/vt-130-vt-134-clear-sealant/>

### Product Description:

A one-component, versatile, acetic cure silicone sealant formulated for glazing and sealing applications where long term reliability is required.

### Applications:

It can be used to bond, seal, repair, and secure various substrates (glass, metal, fabric, vinyl, plastics, weather-stripping, vinyl tops, etc.).

### Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture tube with cap.
2. Apply product to substrate.
3. If used as adhesive: Press firmly and let it cure for six hours before moving it.
4. If used as sealant: Tool within 5 minutes of extrusion.
5. Replace cap after use and store in a cool, dry place.
6. Product can be cleaned with mineral spirit.





### Caution:

Product releases acetic acid during application and curing. Keep out of reach of children. Use in well ventilated areas. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

### Storage:

- Store in a dry and cool place with temperature below 30 °C.
- Use within 24 months from date of production.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company will not accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.

	<b>VITAL TECHNICAL SDN. BHD.</b>	  
	Technical Data Sheet	
	<b>VT-130 / VT-134 Clear Sealant</b>	

Issuance date: 31/03/08

Revision date: 30/09/20

Revision No.: 20-02

**- END -**