

# FLOWFILL PANEL GROUT

# GENERAL PURPOSE NON-SHRINK CEMENTITIOUS GROUT

### 14 November 2017

#### YOUR SMART ADVANTAGES

- Pre-hardening volume-adjusting. Controlled gaseous expansion system compensates for shrinkage and settlement before hardening occurs
- Ready to use, pre mixed, requires only the addition of water
- Enhanced working life
- No metallic iron content to cause staining
- Lower water/cement ratio reduces drying shrinkage, increases durability and reduces permeability
- Can be mixed for stiff, plastic, flowable or fluid application

# DESCRIPTION

General purpose non-shrink (Class A) cementitious grout with enhanced working life, ideal for pre-cast and tilt-panel work.

# APPLICATION

Application thickness 20mm-120mm

# **USES**

All general purpose grouting.
Precast and prestressed panels
Grouting in column based, base infilling.
Filling core holes, rod holes and defects in concrete.
Fill in grout for hollow block walls.
Tilt slab panels.

PRODUCT CHARACTERISTICS		
Colour	Grey	
Size	20kg	
Product code	30840172	

#### **APPLICATION INSTRUCTIONS**

#### **Substrate and Surface Application**

The substrate surface must be clean, sound and free from oil, grease, curing compound or any loose materials. It must be mechanically abraded back to a sound concrete.

- Bolts or anchor holes must be clean and free from dust or loose material. This can be achieved by clean the hole.
- Base plates must be cleared of all rust, oil or grease.
   It is essential to provide air pressure relief holes for venting.

#### Pre-Soaking

It is essential to pre-soak the concrete substrate prior to application of **Bostik Flowfill Panel Grout**. Pre-soak substrate with water for a minimum of 6 hours prior to grouting. Immediately before pouring the excess water should be removed, all water in the anchor and bolt holes must be blown out and no traces of free water present whilst grouting.

#### Formwork

Formwork must be constructed to facilitate rapid and continuous filling, whilst remaining leak proof and water tight. Foam rubber strips or suitable sealants underneath the formwork are recommended.

# **Unrestrained Surface**

As **Bostik Flowfill Panel Grout** is an expanding grout, it is advisable not to have any unrestrained areas.

# **Low Temperature Working**

At temperatures below  $5^{\circ}\text{C}$  the cure rate and strength development rate will be dramatically reduced. If early strength is required, it is advisable to use heated water and condition **Bostik Panel Grout** to  $25^{\circ}\text{C}$ . Do not exceed this temperature.

Bostik Australia Pty Ltd, Level 1, 6 English Street, Essendon Fields, Victoria, 3041, Australia. Tel: +61 3 9279 9333 www.bostik.com.au

Version 1 Page **1** of **3** 

# FLOWFILL PANEL GROUT – General-Purpose Non Shrink Cementitious Grout

#### **High Temperature Working**

At temperatures above 30°C, it is advisable to use water below 20°C when mixing grout. All materials must be kept cool and away from direct sunlight. If practical, the installation area should be shaded by erecting shade screens. If ambient temperatures are excessive, grouting should be scheduled for early morning or late afternoon.

#### Mixing

Bostik Flowfill Panel Grout requires between 3 – 4.4 litres of potable water per 20kg bag, depending on the desired consistency. For optimum results, use a cage or impeller style mixing stirrer powered by a heavy-duty electric mixing drill. Care is to be taken while mixing to avoid the formation of air bubbles.

- Add pre-measured water to a clean mixing bucket.
- Gradually add powder into the water whilst continuously mixing the contents of the bucket. When the entire contents of the bags have been added to the water, mix for a further 3 - 5 minutes to achieve maximum results. Mix product must be smooth, lump free and homogenous consistency.

It is essential that the grouting operation is continuous hence ensure sufficient labour and mixing capacity is available.

Consistency	Water Addition	
	(Litres)	
Stiff	3 Li	
Plastic	3.1 - 3.6 Li	
Flowable	3.6 - 4.0 Li	
Fluid	4.0 - 4.4 Li	

<sup>\*</sup> Consistency is in accordance to ASTM C1107/C1107-11 and AS 1478.2-2005 Table 4.1.2.2

# CAUTION

# DO NOT MIX BY HAND DO NOT ADD ADDITIONAL WATER

Discard any unused grout that has stiffened or hardened. DO NOT RETEMPER

### Pouring

The desired ambient temperature for pouring is approximately 20°C. At this temperature it is essential the grout is placed within 25 minutes of mixing as this will ensure the expansion process is maximised. Ensure the entire area to be grouted is completely filled. We advise the following:

- Use a suitable head box to ensure continuous flow of grout.
- Place/ pour grout from one side, minimizing the likelihood of trapped air.
- The grout head must be maintained at all times so that a continuous grout front is achieved.
- Do not use mechanical vibrators to assist in flow as this will cause segregation of aggregate.

Discard any material that shows signs of stiffening.

#### Curing

On completion of grouting the exposed area should be covered with wet hessian, plastic sheeting or **Bostik Bond 'N' Cure** to prevent excessive moisture loss. At ambient temperature, formwork should be removed no sooner than 24 hours after completion of grouting. The covering should stay in place for a further 6 days. Lack of sufficient curing could result in plastic cracking and drying shrinkage on the surface.

#### **BOSTIK CO OPERATIVE TEST PROGRAM**

Bostik offer a service in which a program has been established to eliminate potential field problems by pretesting Bostik adhesives with samples of building materials to which the adhesive will be applied. This service is available on large projects where pre application testing will aid in determining the proper surface preparation method to achieve optimum adhesion. Consult a Bostik representative for further information.

#### **PROPERTIES**

#### **Application Thickness**

20mm - 120mm

#### **Set Time**

Consistency	Initial Set	Final Set
Stiff	2.5 hours	3.5 hours
Plastic	4 hours	5 hours
Flowable	4.5 hours	7 hours
Fluid	5 hours	8 hours

<sup>\*</sup> Tested in accordance to ASTM C191-08

#### **Time for Expansion**

Start: 15 mins
Finish: 2 - 3 hours
\* Tested in accordance to ASTM C940-98a (re-approved

#### **Compressive Strength**

Consistency	Water			
	Addition	MPa		
	(Litres)	1 day	7 days	28 days
Stiff	3 Li	30-35	50-60	60-75
Plastic	3.1 - 3.6 Li	23-30	40-50	50-60
Flowable	3.6 - 4.0 Li	18-23	30-40	40-50
Fluid	4.0 - 4.4 Li	12-18	20-30	30-40

<sup>\*</sup> Tested in accordance to AS/NZS 2350.11

# FLOWFILL PANEL GROUT – General-Purpose Non Shrink Cementitious Grout

#### Coverage

(Litres per 20kg bag)

Consistency	Yield (Litres)
Stiff	10.5 - 11
Plastic	10.5 - 11
Flowable	11 - 11.5
Fluid	11 - 11.5

#### Fresh Wet Density

Approx 2100 Kg/m3 depending on actual consistency used

#### **Bags Per Cubic Metre**

85 - 90 bags depending on actual consistency used

#### **Pack Size**

20kg

#### STORAGE & SHELF LIFE

Flowfill Panel Grout GP has a shelf life of approximately 12 months in unopened bag. Must be stored in a cool, dry elevated place and protected from high humidity.

#### SAFETY PRECAUTIONS

SEE THE MATERIAL SAFETY DATA SHEET FOR ADDITIONAL INFORMATION.

EMERGENCY INFORMATION: 1800 033 111 (ALL HOURS)

MSDS can be downloaded from www.bostik.com.au

#### CLEAN-UP

Flowfill Panel Grout should be removed from tools and equipment with clean water immediately after use.

# VOC - 0 g/Lt

voccertificates.australia@bostik.com

#### PRECAUTIONS IN USE

Complete details on each of the products mentioned are available on the product Safety Data Sheets. To ensure no harm is caused to persons using Bostik products, it is recommended that all concerned read the appropriate Safety Data Sheets. Visit www.bostik.com/au for copies.

For emergency information contact the Poisons Information Centre, phone 131 126 or the Emergency Response Service, phone 1800 033 111.



This datasheet is for the general help of users. It is provided in good faith. The data is current and accurate to the best of our knowledge. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. Users should carry out tests to decide the product's suitability for purpose. This data sheet and the properties of the product may change without notice. Users, suppliers and retailers should check that the data sheets they have are the latest. To the maximum extent permitted by law, Bostik disclaims all warranties in relation to manufacture and use of the product. Bostik is not liable for representations made by users, suppliers or retailers about the product. Bostik is not liable for any loss or damage resulting from incorrect, careless, or negligent use or storage of the product, including use of out of date product. Any liability arising from use of the product is limited to the replacement or purchase price of the product. Bostik does not exclude rights and remedies that cannot be excluded by legislation, for example under the Australian Consumer Law (ACL). Sale of the product by Bostik is subject to the Bostik Australia Proprietary Limited Conditions and Terms of Sale. For more information on Bostik, products, and conditions of use and sale visit www.bostik.com/au