

ResAlt® H-721072

## Homopolymer Polypropylene

**POLYPROPYLENE**

ResAlt® H-721072 polypropylene resin; white in color - Pelletized

The base resin in this product has not been tested for FDA Code of Federal Regulations of 21 CFR 177.1520.

| Typical Resin Properties | Typical Value | ASTM Method |
|--------------------------|---------------|-------------|
|--------------------------|---------------|-------------|

ResAlt® H-721072: Homopolymer

|  |               |       |
|--|---------------|-------|
| Melt flow rate, dg/min                               | 42-47         | D1238 |
| Tensile strength at yield, psi (MPa)                 | 4400-4600     | D638  |
| Notched Izod impact strength at 73°F, ft-lb/in (J/M) | .3-.5         | D256A |
| Flexural Modulus, psi (MPa)                          | 190000-210000 | D790  |
| Density, g/cm <sup>3</sup>                           | .92-.935      | D792  |
| Ash Content  | .5-1%         | 5630B |

---

(a) Values shown are averages not to be construed as product specifications. These values may shift as additional data are accumulated.  
 (b) Ash content is stated to be talc  
 (c) ASTM methods are the latest under the Society's current procedures. All specimens are prepared by injection molding.

---