

ResAlt® 321026

High Density Polyethylene

High Density Polyethylene

ResAlt® HD-321026 high density polyethylene resin black colored – Pelletized.

The base resin in this product has not been tested for approval with FDA Code of Federal Regulations of 21 CFR 177.1520.

ResAlt® 321026: High Density Polyethylene

Typical Resin Properties	Typical Value	ASTM Method
Melt flow rate, gm/min	.7-.9	D-1238
Tensile strength at yield, psi (MPa)	3600-4000	D-638
Notched Izod impact strength at 73°F, ft-lb/in (J/M)	5-8	D-256A
Flexural Modulus, psi (MPa)	150000-180000	D-790
Density, g/cm ³	.95-.965	D-792
Ash Content	2-6%	5630B

(a) Values shown are averages not to be construed as product specifications. These values may shift as additional data are accumulated.
 (b) ASTM methods are the latest under the Society's current procedures. All specimens are prepared by injection molding.