

# DESIGN FREDOM



HYDROCAL® FGR Gypsum Cement— A strong, thin gypsum cement that provides unlimited architectural possibilities.





Whether your next design project is restoration, new construction, or high-end residential, HYDROCAL® FGR Gypsum Cement from United States Gypsum Company can open the door to many three-dimensional possibilities. A great variety of finished items, formerly made from conventional plaster, wood, concrete, stone, and other materials, can be duplicated, often at less cost using the unique properties of HYDROCAL FGR Gypsum Cement.

Used for Glass-Reinforced Gypsum (GRG) fabrication, HYDROCAL FGR
Gypsum Cement is an alpha-hemihydrate gypsum-based material that has a low
water demand. This results in high strength, high density pieces that can be
fabricated for a variety of interior architectural applications, such as column
covers, light coves, wall and ceiling moldings, cornices, coffers, and more. And
because it is made by a company with almost 100 years of experience in the
building industry, you can be sure that you are getting the best product available.


HYDROCAL FGR Gypsum Cement sets fast, develops high strength, and permits fabrication of strong, resilient glass-reinforced gypsum products. These durable products are fire-resistant, are adaptable to deep patterns, accept most coatings, help overcome the building fire code problems of many plastics, and cost about 2/3 less than filled polyesters.


And the design possibilities are endless: The economical price and fabrication flexibility allow you to duplicate existing pieces for renovation projects or create your own masterpieces quickly and easily.






# LIGHT











HYDROCAL FGR Gypsum Cement can be cast into lightweight, interior architectural elements, like these tent-shaped light coves, giving you the freedom to change the atmosphere of a space without expensive reinforcement costs.




HYDROCAL FGR Gypsum Cement provides
fabrication flexibility, making it easy to
produce everything from simple, elegant cornices to
richly ornate capitals and medallions.









HYDROCAL FGR Gypsum Cement erases limitations when renovating damaged areas without compromising historical beauty—architectural design elements can be pre-cast offsite from original pieces to exacting detail and easily decorated with a wide range of finishes.

- HYDROCAL® FGR Gypsum Cement's great looks combine with the following features to provide all the design freedom you need:
- Versatile—An easily decorated surface accepts most oil-base, alkyd, or latex paints, and most stains, lacquers, varnishes, or shellacs to create just the right finish for your application.
- Thin and Lightweight—1/10 in. thick HYDROCALFGR Gypsum Cement panels weigh only 9 to 10 lb. per sq. ft., reducing the costs of reinforcing the building.
- Strong—Because HYDROCALFGR Gypsum Cement is reinforced with glass fibers it is strong and durable. Test results show a flexural strength of 4,000 psi, flexural modulus of 2.1x106 psi, and impact strength of 8.0 to 8.8 ft. lb./in.†
- Fire Resistant—Laboratory fire tests conducted on varying thicknesses of HYDROCALFGR

  Gypsum Cement (with 5% glass fiber content and without face coating) substantiate

  its noncombustibility and show no appreciable fuel contribution and zero flame

  spread. (The tests were conducted in accordance with ASTM E136-94A "Standard

  Test Method for Behavior of Materials in a Vertical Tube Furnace at 750 °C")
- Easy to Install—HYDROCALFGR Gypsum Cement can be precast off-site allowing less work in the field and reduction of on-site costs.

#### **Comparative Tests**

The following table compares typical physical test results of glass-reinforced gypsum with other products for related uses:

	Density	Flexural Strength	Modulus of Elasticity	Impact	Fiber Content
Products	(lb./ft³)	(psi)	(x 10 <sup>6</sup> psi)	(ft. lb./in.)	(wt. %)
Glass-Reinforced Gypsum	103-112	3200-4000	2.1-2.2	8.0-8.8	5-6
Plaster of Paris	72	900	0.68	4.8-5.0	
Fiber-Reinforced Plastics	91	18000	0.8	13.0	25
Hardboard <sup>1</sup>	53/58	3800/4400	0.46/0.56	3.4/4.3	97
Gypsum Board <sup>1</sup>	44	420/1400	0.1/0.2		
Plywood	38	2000	1.6		

<sup>1</sup>Properties may vary with the direction of fabrication. Thus, properties for both directions are given.

**Typical Physical Properties** 

71 - 7			
Matrix	HYDROCAL FGR Gypsum Cement		
Set Time	90-120 min. (FGR-115, spray application)		
	50-70 min. (FGR-95, hand application)		
Consistency	25-30 cc		
Glass Fiber	5-6% by weight Type E chopped to 3/" length		
Flexural Strength	3200-4000 psi		
Modulus of Elasticity in Flexure	2.1-2.2 x 10 <sup>6</sup> psi		
Ultimate Tensile Strength	1200-1400 psi		
Modulus of Elasticity in Tension	2.7-3.8 x 10 <sup>6</sup> psi		
Impact Strength	8.0-8.8 ft. lb./in. <sup>†</sup>		
Thermal Conductivity	4.0-4.2 Btu x in./hr. x ft. <sup>2</sup> °F		
Specific Heat	0.253 Btu/lb. °F		
Flammability	Zero flame spread. Zero smoke contribution. (Per ASTM 136-94A.)		
Rockwell Hardness	M72		
Dielectric Strength	Same as air when dry; conductive when wet		
Density	103-112 lb./ft. <sup>3</sup>		
Thermal Coefficient of Expansion	8.3 x 10 <sup>-6</sup> in./in./°F		
Coverage	100 lb. of Hydrocal FGR Gypsum		
	Cement 125 ft. <sup>2</sup> - 1/10" thick		

†Modified Charpy method per ASTM D256-93A.

#### **Architectural Specifications**

#### Part I—General 1.01 Scope

This specification for Hydrocal FGR Gypsum Cement is a guide in the preparation of a specification which can be adapted to specific projects and conditions. These specifications are not intended to cover every possible job condition, but rather to assist in preparation of specifications.

#### 1.02 Related Systems

A. Gypsum board systems. Section

В.	Paint	systems.	Section
----	-------	----------	---------

C. Acoustical systems. Section

D. Plaster systems. Section \_

E. Work installed but furnished under other sections. Section . .

F. Work furnished but installed under other sections. Section . . .

#### 1.03 Quality Assurance

- A. Subcontractor qualifications: Part manufacturer shall have not less than three years of successful experience in the manufacturing and molding of glass-reinforced gypsum. Installer shall have not less than three years successful experience in the installation of the specified work and be acceptable to the part manufacturer.
- B. Requirements of regulatory agencies: Codes and regulations of authorities having jurisdiction.

#### 1.04 References

- A. ASTM C11: Terminology relating to gypsum and related building materials and systems.
- B. ASTM CXXX/XXXM<sup>1</sup>: Standard Specification for FGR Glass and Fiber Reinforced Gypsum Parts.
- C. ASTM CXXX/XXXM1: Standard Specification for Molded Glass Fiber Reinforced Gypsum Parts.
- D. ASTM E84: Test Method for Surface Burning Characteristics of Building Materials.
- E. CISCA "Glass Reinforced Gypsum, A Guide."

#### 1.05 Submittals

A. System details: Submit manufacturer's catalog cuts, literature of standard drawings showing details of the system with product conditions clearly identified, and manufacturer's recommended installation instructions.

- B. Shop drawings: Submit full, complete detailed shop drawings for all HYDROCAL FGR Gypsum Cement construction. Submit shop drawing details and reflected ceiling plans if necessary, to indicate ceiling modules and related lighting and mechanical systems. Show dimensional location of framing and support details for HYDROCAL FGR Gypsum Cement items supported by suspension systems.
- C. Samples: Submit HYDROCAL FGR Gypsum Cement panel finishes to architect for acceptance.

#### 1.06 Delivery, Storage, and Handling

- A. Raw materials: All raw materials, except water, shall be delivered and stored in their original unopened packages in an enclosed shelter providing protection from damage and exposure to the elements. Damaged or delivered materials shall be removed from the premises.
- B. Finished materials:
  - Deliver materials in original unopened containers, clearly labeled with manufacturer's name, item description, specification number, type, and class, as applicable.
  - 2. Storage time on the job site should be as short as possible, and environmental conditions should be as near as possible to those specified for occupancy. Excess humidity during storage can cause expansion of the installation. Chemical changes in the reinforcement mat and coating can be aggravated by excess humidity and cause discoloration when storing even unopened containers. Damaged or deteriorated materials shall be removed from the premises. Immediately before installation, store items at a location where temperature and humidity conditions duplicate ambient during installation and anticipated for occupancy.
  - Installation conditions should be at or near those under standard occupancy conditions of temperature and humidity 60-85 °F (16-29 °C), no more than 70% relative humidity.
  - 4. Handle in such a manner as to ensure against racking distortion or physical damage of any kind.

#### 1.07 Project Conditions

- A. Existing conditions: (Include specific alteration work to be completed for project.)
- B. Environmental requirements: Building shall be enclosed with all windows and exterior doors in place and glazed, and the roof watertight before installation of HYDROCAL FGR Gypsum Cement

- systems. Wet work shall be in place, completed and nominally dry with HVAC system in continuous operation. Maintain climate conditions to range from 60-85 °F (16-29 °C) and relative humidity of not more than 70% before installation of HYDROCAL FGR Gypsum Cement system.
- C. Coordination with other work:
  - Coordinate with other work supported by or penetrating through ceiling, including mechanical and electrical work and partition systems.
  - Duct work above suspension system and behind wall systems shall be complete and permanent heating and cooling systems operating.
  - Installation to conduit above suspension system and behind wall systems shall be complete before installations of HYDROCAL FGR Gypsum Cement System.
  - D. Protection: Protect all completed HYDROCAL FGR Gypsum Cement system work from damage.

### Part II—Products 1.01 Manufacturer and Materials

- A. Alpha-calcium sulfate hemihydrate plaster: HYDROCAL FGR-95 or 115 Gypsum Cement as manufactured by United States Gypsum Company, Industrial Gypsum Division, Chicago, Illinois, U.S.A.
- B. Glass fiber reinforcement: "E" glass fiber (%" long chopped glass fiber strands or continuos strand mats of calcia-alumina silicate glass) which conforms to test method D578.
- C. Water: Potable without impurities that affect the setting of gypsum cements.
- D. Mixing
- Combine and mix HYDROCAL FGR Gypsum Cement to water according to United Stated Gypsum Company's recommendations to form a slurry.
- Combine the slurry with not less than 5% by weight glass fiber reinforcement to form the architectural detail not less than \( \lambda'' \) in thickness.
- E. Accessories
  - Fasteners and inserts: As recommended by the engineer and or fastener manufacturer for specific application.
  - 2. Adhesive: As recommended by manufacturer where required.
  - 3. Sealant: SHEETROCK® brand Acoustical Sealant.
  - 4. Joint treatment: See Product Folder SA927 Gypsum Panels & Accessories.
    SHEETROCK Joint Tape
    SHEETROCK Fiberglass Drywall Tape

- SHEETROCK Setting-Type (DURABOND®) or Lightweight Setting-Type (EASY SAND™) Joint Compounds.
- F. Performance:
  - 1. Shell thickness minimum ½" thickness
  - Surface burning characteristics:
     Material shall be noncombustible having a flame spread/smoke developed values less than 0/10.

## Part III—Execution 1.01 Installation:

- A. Installer must verify actual field dimensions prior to installation.
- Install in accordance with CISCA recommendations, and local building codes
- C. Install in accordance with manufacturer's current printed recommendations.
- D. Install all HYDROCAL FGR Gypsum Cement panels true plumb and level and in accordance with approved shop drawings.
- E. Fasteners as recommended by fastener manufacturer for specific job conditions.

All cast work (except Nashville work) courtsey of McNulty Bros., Chicago, Illinois.

Nashville cast work and photos courtesy of Cast Design & Supply, Shelbyville, Tennessee.

**SAFETY FIRST!** Follow good safety and industrial hygiene practices during handling and installing of all products and systems. Take necessary precautions and wear the appropriate personal protective equipment as needed. Read material safety data sheets and related literature on products before specification and/or installation.

**NOTICE:** We shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.,

The following are trademarks of United States Gypsum Company: DURABOND, EASY SAND, HYDROCAL, SHEETROCK, USG.

### **United States Gypsum Company**

Industrial Gypsum Division 125 South Franklin Street Chicago, Illinois 60606-4678 Technical Assistance: (800) 487-4431

©1996, United States Gypsum Company IG338/119