

# INTAMSYS® PA12-CF

## Product Description

INTAMSYS® PA12-CF is a carbon fiber reinforced PA12 (Nylon 12) filament. Thanks to the low moisture sensitivity of PA12, this product features outstanding mechanical and thermal properties even after the moisture conditioning process.

PHYSICAL PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUE
Density	ISO 1183	g/cm <sup>3</sup>	1.06
Glass transition temperature	DSC, 10°C /min	°C	108
Melting temperature	DSC, 10°C /min	°C	165
Heat deflection temperature	ISO 75 1.8MPa	°C	105
Melt index	280°C, 2.16 kg	g/10min	25

MECHANICAL PROPERTIES <sup>1</sup>	TEST METHOD	UNITS	TYPICAL VALUE
Tensile strength	ISO 527	MPa	69.3
Young's modulus	ISO 527	MPa	3748
Elongation at break	ISO 527	%	2.9
Flexural strength	ISO 178	MPa	114.1
Flexural modulus	ISO 178	MPa	3532
Impact strength	ISO 179, Notched	kJ/m <sup>2</sup>	12.1

Note:

- All testing specimens were printed using a FUNMAT HT 3D PRINTER under the following conditions:  
 Printing temperature = 270 °C, printing speed = 45 mm/s, number of shells = 2, and 100% infill.  
 All specimens were annealed at 80°C for 24h and dried for 48h prior to testing.

## Disclaimer

The typical values presented in this document are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End-use performance of printed parts properties can be impact by, but not limited to, part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of INTAMSYS materials for the intended application. INTAMSYS makes no warranty of any kind, unless announced separately, to the fitness for any particular use or application. INTAMSYS shall not be made liable for any damage, injury or loss induced from the use of INTAMSYS materials in any particular application.