

FORTIS

SESTAVA ZGORNJE/SPODNJE TKANINE COMPOSITION SURFACE/BACK SIROVINSKI SASTAV GORNJE/DONJE TKANINE ZUSAMMENSETZUNG DER OBERE/UNTERE SEITE COMPOSIZIONE TESSUTO SUPERIORE/INFERIORE		100% POLIESTER / 95% POLESTER, 5% BOMBAŽ 100% POLYESTER / 95% POLYESTER, 5% COTTON 100% POLIESTERSKO VLAKNO / 95% POLIESTERSKO VLAKNO, 5% PAMUK 100% POLYESTER / 95% POLYESTER, 5% BAUMWOLLE 100% POLIESTERE / 95% POLIESTERE, 5% COTONE	
ŠIRINA WIDTH ŠIRINA BREITE ALTEZZA	145 cm	TEŽA WEIGHT TEŽINA GEWICHT PESO	305 gr/m ²
TEST	STANDARD	REZULTAT/RESULTS/REZULTAT/ERGEBNIS RISULTATI	
		OSNOVA/WARP/ OSNOVA/KETTE/ORDITO	VOTEK/WEFT/ POTKA/SCHUSS/TRAMA
RAZTEZNA TRDNOST TENSILE STRENGTH ČVRSTOČA NA RASTEZANJE ZUGFESTIGKEIT RESISTENZA ALLA TRAZIONE	EN ISO 13934-1	31,6 %	26,9 %
RAZTRŽNA TRDNOST TEAR STRENGTH ČVRSTOČA NA KIDANJE WEITERREISSFESTIGKEIT RESISTENZA ALLA LACERAZIONE	EN ISO 13937-3	127,6 N	114,1 N
DRSNOST NITI RESISTANCE TO SEAM SLIPPAGE OTPORNOST NA POMJERANJE /POMERANJE ŠAVA NAHTSCHIEBEWIDERSTAND RESISTENZA ALLO SCORCIMENTO DELLA CUCITURA	prEN ISO 13936-2 PRI/AT/KOD/BEI 180 N	4,0 mm	4,0 mm
OBSTOJNOST TKANINE NA DRGNJENJE ABRASION RESISTANCE POSTOJANOST TKANINE NA TRLJANJE SCHEUERBESTAENDIGKEIT RESISTENZA TESSUTO ALL'ABRASIONE	DIN EN ISO 12947-1 DIN EN ISO 12947-2	>100.000 OBRATOV/REVS./OBRTAJA /TOUREN/GIRI	
PILING PILLING RESISTANCE PILING PILLBILDUNG RESISTENZA PILLING	EN ISO 12945-2 2.000 OBRATOV/REVS./OBRTAJA /SCHEUERTOUREN/GIRI	5	
OBSTOJNOST BARVE NA SVETLOBO COLOUR FASTNESS TO LIGHT POSTOJANOST BOJE NA SVJETLO/SVETLOST LICHTECHTHEIT RESISTENZA ALLA LUCE	EN ISO 105-B02 Method 2	5	
OBSTOJNOST BARVE NA DRGNJENJE COLOUR FASTNESS TO RUBBING POSTOJANOST BOJE NA TRLJANJE REIBECHTHEIT RESISTENZA COLORI ALL'ABRASIONE	EN ISO 105-X12	SUHO/DRY/SUHO/ SUVO/TROCKEN/SECCO	MOKRO/WET/ MOKRO/NASS/UMIDO
		4-5	5
VSEBNOST AZO BARVIL CONTAIN OF AZO DYES SADRŽAJ AZO BOJA AZOFARBSTOFFE CONTENUTO DI COLORANTI AZOICI	§ 64 LFGB 82.02-2,3,4,9	NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE	

MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631
Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si

VSEBNOST BARVIL, KI POVZROČAJO ALERGIJE ALERGY CAUSING DYES SADRŽAJ BOJA KOJE UZROKUJU ALERGIJE ALLERGISIERENDE FARBSTOFEE CONTENUTO DI COLORANTI ALLERGENICI		NI ZAZNANA NOT DETECTABLE NE SADRŽI NICHT NACHWEISBAR NON RILEVABILE
TEST NEGORLJIVOSTI FIRE RETARDANT TEST NEGORIVOSTI BRENNVERHALTEN IGNIFUGO	BS 5852 part 1 Ignition source 0	PRESTAL TEST PROŠAO TEST PASSED UEBERSTANDEN SUPERATO

ZAŠČITA TKANINE:	VODOODBOJNI NANOS
ZAŠTITA TKANINE:	VODOODBOJNI NANOS
FABRIC PROTECTION:	WATER REPELENT
STOFFSCHUTZ:	WASSER ABWEISEND
PROTEZIONE TESSUTO:	IDROREPELENTE

MED BARVNIMI PARTIJAMI SO MOŽNA ODPSTAPANJA V BARVI
COLOUR DIFFERENCES BETWEEN DYING LOTS ARE POSSIBLE
MOGUČA SU ODPSTAPANJA U BOJI KOD PROIZVODNJE
FARBNIANSEN SIND MOEGLICH
DIFFRENZE DI COLORE TRA I LOTTI DI TINTURA SONO POSSIBILE.



MERCIS d.o.o., Puchova ulica 3, 1235 Radomlje, Slovenija ID: SI13107631
 Tel. +386 1 4700700 Fax +386 1 4700720 e-mail:mercis@mercis.si