



---

## DuPont™ Tyvek® Supro - wall installation

---

NBS: H92 785, P10 320

Also: H20, H21, H30, H31, M30

For additional information on our product(s) and guidance on how to use them you may wish to refer to our step by step Installation Guide and videos. This and other useful information is on our web site:

[www.building.dupont.co.uk](http://www.building.dupont.co.uk)

For help with a project please contact the DuPont Building Knowledge Centre. (Contact details can be found at the end of this Installation Sheet).

**Breather Membrane** to EN 13859-2 shall be **Tyvek® Supro** as supplied by DuPont Performance Building Solutions, Bristol & Bath Science Park, Dirac Crescent, Emersons Green, Bristol. BS16 7FR.

### **Storage**

Rolls should be stored palletised on a smooth clean surface, under cover and protected from direct sunlight.

### **General**

Care should be taken when handling the membrane to prevent tears and punctures occurring. Any that do occur should be repaired with Tyvek® Acrylic Tape (2060B).

### **Orientation**

Unroll Tyvek® Supro horizontally over the face of the construction with the printed logo facing outwards. Ensure maximum coverage by extending 100mm min below the sheathing, CP board or lowest structural timber/steel member.

### **Free hanging condition**

Tyvek® Supro may be fixed in a self-supporting condition, spanning between vertical or horizontal members. Maximum span should not exceed 1.2m in a protected environment, or 600mm if exposed to wind loading.

### **Initial fixing**

Tyvek® Double sided (acrylic) Tape (50mm) may be used to provide an initial fix for Tyvek® Supro, but mechanical fixings (see below) must be made almost immediately after. Permanent security of the membrane may also be made with external insulation, battens or cladding brackets. Extra care should be taken where the membrane is exposed to high wind conditions.

### **Fixing – to timber studs/sheathing**

Fix Tyvek® Supro with stainless steel staples or corrosion resistant nails. Fix membrane at 600mm centres horizontally, 300mm centres vertically and at 150mm centres at joints and openings.

### **Fixing - to masonry**

Tyvek® Supro may be fixed to masonry with a suitable anchor fixing system or a masonry nail/screw and EPDM rubber washer. Fixings should be at maximum 500mm centres. Tyvek® Butyl Tape (double sided) may be used to fix the membrane in addition to the mechanical methods suggested above. Tyvek® Primer can be applied to chalky or porous masonry to seal the surface and improve adhesion before applying adhesive tape.

### **Fixing - to steelwork (SFS)**

Initial (temporary) fixing of Tyvek® Supro may be made with continuous strips of Tyvek® Double Sided (acrylic) Tape. These should be supplemented with mechanical fixings through to the steel structure, where suitable drill-tip or self-tapping screws may be used. The screws must sit flush (not countersunk) and a rubber or EPDM washer should sit between the screw heads and the membrane to avoid water ingress. Screw fixings should be spaced vertically at 500mm centres on every stud (typically spaced at 600mm horizontal centres).

### **Fixing - Rainscreen Cladding Applications**

Tyvek® Supro may be fixed to the external face of a cement bonded particle board, OSB or ply sheathing, using a combination of Tyvek® Double sided (acrylic) Tape and stainless-steel staples. Tyvek® Supro may also be secured by fixing through the sheathing to the underlying structure using suitable drill-tip or self-tapping screws. See Fixing - to steelwork (SFS) above.

In many cases, the retrospective fixing of timber battens or metal brackets (& insulation) will provide the principle security for the membrane. Care should be taken to ensure these components are fixed tightly over the membrane to avoid water ingress. If in doubt Tyvek® Butyl Tape may be used between the component and the membrane.

### **Fixing to insulation**

Fix Tyvek® Supro to rigid insulation with a proprietary Tyvek expanding insulation fixing anchor at maximum 500mm centres. Penetrations made by wall ties or cladding brackets must be made good with either Tyvek® Acrylic Tape (2060B) or Tyvek® FlexWrap EZ.

### **Laps**

All horizontal laps should be 100mm min. Vertical laps should be 150mm min.

### **External corners**

Dress Tyvek® Supro around external corners ensuring a return of 300mm min.

### **Window openings**

Wrap Tyvek® Supro into window/door openings and seal to frame with Tyvek® Acrylic Tape (2060B) or Tyvek® Plastering Tape if render is later to be applied. Make good to corners using Tyvek® FlexWrap EZ.

### **Cavity barriers/trays/flashings**

Dress Tyvek® Supro over cavity barrier/tray/flashings ensuring a minimum lap of 100mm.

### **Floor junctions**

Dress Tyvek® Supro over intermediate floor zone ensuring a minimum lap of 100mm between sheets

### Airtightness – sealing (optional)

Tyvek® Supro has been tested for 'Resistance to penetration of air' in accordance with EN 12114 and achieved <0.25 m<sup>3</sup>/h.m<sup>2</sup> at 50 Pa. With all laps and penetrations sealed, Tyvek® Supro will contribute to the overall airtightness of the building.

Seal the laps in Tyvek® Supro with Tyvek® Acrylic Tape (2060B) or Tyvek® Double Sided (acrylic) Tape. Fixing penetrations can be sealed by applying Tyvek® Butyl Tape to the substrate before the membrane is installed. Complicated penetrations may be sealed using Tyvek® FlexWrap EZ.

**Compatibility:** Where timber treatments are used care should be taken to ensure they are touch-dry before the installation of the Tyvek® membrane. Retrospective spray applied micro emulsions can also pose significant risk to polymer-based materials such as Tyvek® Supro. Masking the membrane against such preservative treatments should be considered.

### Temporary exposure period

Tyvek® Supro may be left exposed for a period not exceeding **4 months**, provided that the membrane is adequately secured in accordance with our recommendations. Site conditions and exposure to wind should be assessed to determine whether extra security measures for the membrane are required.

### Fire regulations

Tyvek® Supro has Fire Classification E in accordance with EN 13501-1. Care should be taken to determine suitability of this membrane for the intended application, with specific regard to building height and proximity to boundary. Users/specifiers should refer to their regional regulatory guidance documents in case there are any requirements or variations that may restrict the use of this product.

Video installation link: <https://www.dupont.co.uk/resource-center.html?BU=pbs&restype=video>

---

#### DuPont™ Tyvek® Building Knowledge Centre (BKC) – EMEA

Bristol & Bath Science Park  
Dirac Crescent  
Emersons Green  
Bristol, UK  
BS16 7FR

Technical: 0117 970 9454/9455

Sales: 0117 970 9456

Technical enquiries: [tyvek.construction@dupont.com](mailto:tyvek.construction@dupont.com)

[www.building.dupont.co.uk](http://www.building.dupont.co.uk)



THE DUPONT™ TYVEK®  
BUILDING KNOWLEDGE CENTRE

- *Science you can build on* -

[www.building.dupont.co.uk](http://www.building.dupont.co.uk)  
[www.energy-efficiency.dupont.com](http://www.energy-efficiency.dupont.com)

Recommendations as to methods, use of materials and construction details are based on the experience and current knowledge of DuPont and are given in good faith as a general guide to designers, contractors and manufacturers. This information is not intended to be a substitute for any testing you may need to conduct to determine, for yourself, the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge, regulations and experience becomes available since we cannot anticipate all variations in actual end-use conditions. DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a licence to operate under a recommendation to infringe any patent right.

Tyvek® construction membranes are manufactured by DuPont under an ISO 9001: 2015 Quality Assurance System.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2021 DuPont.