



# PSA-Backed Aluminized Fiberglass

**THERMAL CONTROL PRODUCTS, INC.**

## Description

This product is a lamination of fiberglass fabric and aluminum foil with a pressure sensitive backing for use in automotive and industrial heat shields.



### Key Benefits:

- Self-adhering
- Fiberglass fabric, aluminum foil laminate and pressure-sensitive adhesive construction
- Excellent protection against radiant heat
- Die-cut, tape or custom sized designs available
- \* Actual heat resistant properties are application specific

## Characteristics:

- Reflects 90% of radiant heat energy
- Recommended continuous operating temp. 400°F
- Maximum short-term exposure temp. 1000°F

## Property Data

Characteristic	Method	Values*	
		English	Metric
Weight	ASTM-D-3776	12.2 – 14.76 oz/sq yd	457 g/m <sup>2</sup> ± 9.5%
Thickness	ASTM-D-1777	0.017 – 0.023 in	0.509 mm ± 0.075 mm
Tensile Strength	ASTM-D-5035	Warp 200 lbs/in Min Fill 125 lbs/in Min	35.72 kg/cm 22.33 kg/cm
Tear Strength	ASTM-D-5587	Warp 25 lbs Min Fill 25 lbs Min	11.34 kg 11.34 kg
Mullen Burst	ASTM-D-3786	200 psi Min	21 kg/cm <sup>2</sup>
PEEL Adhesion	PSTC-1	3.5 lbs/in	
Cut Tolerance			± 3 mm
Color and Coating		Aluminum Foil	
Base Fabric and Weave		Fiberglass/Plain Weave	

\*All values are nominal unless otherwise specified.

\*\*Information provided by supplier.

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.

