


ACRATRIM SATIN ACRYLIC ENAMEL

RESOURCE CODE 210004
MAY 2019
PAGE 1 OF 3



Description & Uses

Baxta Acratrim Satin Acrylic Enamel is a 100% acrylic interior and exterior trim and wall paint that provides the speed and ease of water-based technology in a tough durable enamel coating. This smooth satin finish is non-yellowing and dries hard so painted surfaces will not stick together. Suitable for use in most areas where oil-based enamels were traditionally used. Not suitable for areas which will be subjected to hot objects, e.g. benchtops.

Features & Benefits

- | | |
|---|--|
| <ul style="list-style-type: none"> • Durable finish • Fast drying | <ul style="list-style-type: none"> • Low VOC • Non-yellowing |
|---|--|

Colours & Gloss

White – Can be tinted to White Base colours.

Satin (Gloss level 25 - 35 at 60 degrees).

Environmental Data & Certifications



Approved to Australia Paint Approval Scheme Specification APAS 0260/2.
Australian Standard AS3730.2.

ACRATRIM SATIN ACRYLIC ENAMEL

RESOURCE CODE 210004

MAY 2019

PAGE 2 OF 3

Properties & Performance Guide	
Dry & Recoat Times	Surface Dry - 30 minutes Recoat - 2 hours Fully Cured - 7 days Figures are quoted at 25°C and at 50% humidity. Drying will take longer at lower temperatures or higher relative humidity.
Coverage per Coat	Up to 16 M ² /L depending on the surface texture, porosity and method of application.
Thinning	Thinning is generally not recommended unless spraying; add up to 100ml clean water per litre of paint to achieve acceptable atomisation. Up to 50ml of clean water per litre of paint can be added to ease application in warm weather.
Clean Up	Clean up with cold water away from drains. Protect Our Environment: Do not pour leftover paint down the drain. To dispose of unwanted paint see paintback.com.au . Empty paint containers should be left open in a well ventilated area to dry out. When dry, recycle containers via recycling programs. Check with your local council first.
VOC (Volatile Organic Compounds)	VOC < 45g/Litre.

Recommended Substrate Conditions & Preparation
<p>Work Area: Care should be taken to keep product off windows and adjacent surfaces that are not to be coated, as product can be very difficult to remove once allowed to dry. Use drop sheets to cover surroundings surfaces. Ensure air movement and ventilation while painting. Keep doors and windows open.</p> <p>Substrate Condition: Recommended surfaces include previously painted surfaces, sound water-based surfaces and pre-primed MDF. Bare surfaces required undercoat (dependant on substrate). Baxta Acratrim Satin Acrylic Enamel must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.</p> <p>Surface Prep: Surfaces should be clean, dry and free from loose or crumbling material, oil and release agents. Repair any damaged areas, fill cracks, nail holes and imperfections. Prime bare paper-faced plasterboard, timber, masonry and metal surfaces with appropriate undercoats or primers before application. Previously painted surfaces should be sanded to a dull finish.</p>

Application Guide
<p>Stir well before and during use with a broad paddle reaching to the bottom of the can and using an upward lifting action.</p> <p>Apply a minimum two full, even coats by brush, roller or airless spray. Use a short nap (6-9mm) synthetic roller or quality synthetic brush. Moisten brushes or rollers lightly before use, and to keep them working freely, rinse occasionally in clean water. Spread the paint quickly to an even film over a small section, laying off lightly into freshly painted sections. Avoid applying excessively thick coats as running or sagging may occur. Splashes should be removed immediately with a damp cloth. To achieve a smoother finish, lightly sand after undercoating and between finishing coats with 240 or finer abrasive paper and remove dust. It is important to maintain a wet edge when applying to avoid tracking and picture framing. Baxta Acratrim Satin Acrylic Enamel must be applied evenly and consistently to provide colour consistency and opacity. Do not apply when temperature is below 10°C or above 35°C or when humidity is very high. Drying time may be longer in cold or humid conditions. Do not apply when rain or dew is likely. Keep sheltered from frosts and rain for a minimum 48 hrs after completion dependent on climatic conditions.</p>

ACRATRIM SATIN ACRYLIC ENAMEL

RESOURCE CODE 210004
MAY 2019
PAGE 3 OF 3

Additional Data

Available in 10L.
Check colour is correct before applying. Manufacturer and distributor will accept no liability once product has been applied. For large projects box (or mix) pails to ensure colour consistency.
Avoid exposure to steam and condensation for 48 hours after application of final coat.
Leave 7 days after application of final coat before washing. Wash using a sponge or soft cloth with warm water and mild detergent. Avoid harsh scrubbing and strong household cleaners.
Containers must be secured and stored upright during transit.
Containers must not be exposed to excessive heat or cold.
Store in a secure, cool and well ventilated place. Keep container tightly closed.
Do not use for any other purpose other than as specified.

Manufacturers Comment

This product has been designed as part of a totally integrated coating system. Failing to follow application instructions or use with other manufacturer's product, could result in detrimental effects on product performance for which Baxta Industries Pty Ltd cannot be held responsible.

Safety Data

First Aid Instructions

For advice, contact the Poisons Information Centre on 131 126 (Australia) or a doctor.
If in eyes, wash out immediately with water. Remove contact lenses if present and easy to do so, continue rinsing.
If skin contact occurs remove contaminated clothing and flush contaminated skin with water.
If inhaled remove from contaminated area to fresh air.
If swallowed, do not induce vomiting. Give a glass of water to drink.

Safety Directions

Keep out of reach of children.
Avoid contact with skin and eyes.
Ensure adequate ventilation during use.
Avoid prolonged breathing of vapour.
Wash hands thoroughly after use.

Further Information

Safety Data Sheet and Product Information can be found at www.baxta.com.au or by calling 1300 85 55 40.