

## ULTRA PREMIUM

### Ultratrim Acrylic High Gloss

Product Code: UTG

#### Product Description

Ultratrim Acrylic Enamel is a low-odour, fast drying trim paint with unique water based technology that provides a tough, durable enamel coating. It is simple to use, hard wearing, non-chipping and non-yellowing formula with a quick 2 hour recoat. The excellent flow and levelling ensure a smooth finish that is easy to clean. Ultratrim Acrylic Enamel can be used for Interior and Exterior surfaces providing a long lasting finish that has the convenience of water wash up.



#### Product Features

- ✓ Fast drying
- ✓ No lingering odour
- ✓ Tough, durable finish
- ✓ Non-yellowing

#### Where to use

Interior and Exterior trim areas including skirting boards, architraves, windows, doors, furniture and contact areas where a hard wearing finish is required. Typical substrates include timber, MDF, galvanised iron and Zinalume®.

#### Typical Properties

Gloss	75 – 80 @ 60°
Application tools	Brush, roller, spray
Wash up	Water
Dry Time	Touch dry 20 minutes Recoat 2 hours
Coverage	Up to 16m <sup>2</sup> /L
Colour	White, UDT, DKT, EDT, GT, RDT, BBT, OX, YX. Available sizes may vary.
Sizes	500ml, 1L, 2L, 4L, 10L
Approvals	APAS 0260/1
VOC	55 g/L
Volume solids	36%
Film Build per coat	Wet 63 um Dry 22 um

#### Surface Preparation

General Surface Preparation	<ol style="list-style-type: none"> <li>1. Fill cracks, nail holes and imperfections with Haymes Unifill.</li> <li>2. Scrape all loose/flaking paint. Sand smooth &amp; dust down. All surfaces must be clean, bare, dry and free of wax, grease and other contaminants.</li> <li>3. Prime bare timber and metal areas with appropriate undercoats or primers.</li> </ol>
Previously Painted Surfaces	<ol style="list-style-type: none"> <li>1. Prepare any damaged areas as for General Surface Preparation.</li> <li>2. Sand gloss surfaces to a dull finish and remove all dust</li> <li>3. Apply one coat of Haymes Ultracover</li> </ol>
MDF	<ol style="list-style-type: none"> <li>1. Prepare any damaged areas as for General Surface Preparation.</li> <li>2. Check that any pre primers are suitable for painting by cutting an "X" through the</li> </ol>

	<p>coating. Press tape over the "X" and pull off sharply. If any coating is stuck to the tape then the pre primer must be fully removed by sanding prior to any further painting.</p> <ol style="list-style-type: none"> <li>Sand smooth and remove all dust.</li> <li>Apply one coat of Haymes Ultraseal or Ultracover.</li> </ol>
Timber	<ol style="list-style-type: none"> <li>Prepare any damaged areas as for General Surface Preparation.</li> <li>Apply one coat of Haymes Ultracover or for tannin rich timbers apply one coat of Haymes Ultralock.</li> </ol>
Aluminium	<ol style="list-style-type: none"> <li>Wash with Haymes Unikleen &amp; rinse with clean water.</li> <li>Abrade the surface with a scourer.</li> <li>Apply one coat of Haymes Ultracover.</li> </ol>
Galvanised Iron	<ol style="list-style-type: none"> <li>Degrease</li> <li>Wash with Haymes Unikleen &amp; rinse with clean water.</li> <li>Apply one coat of Haymes Ultracover.</li> <li>Structural galvanized steel requires mechanical abrasion and 1 coat of Haymes Ultraprime.</li> </ol>
Zincalume®	<ol style="list-style-type: none"> <li>Wash with Haymes Unikleen &amp; rinse with clean water.</li> <li>Apply one coat of Haymes Ultracover.</li> </ol>
Steel & Wrought Iron	<ol style="list-style-type: none"> <li>Prepare any damaged areas as for General Surface Preparation.</li> <li>Remove all traces of rust.</li> <li>Apply one coat of Haymes Ultraprime.</li> <li>Apply one coat of Haymes Ultralock or Ultracover.</li> </ol>

### Application

- Do NOT apply if ambient temperature is less than 10°C or greater than 30°C or if conditions will drop below 10°C during the drying period. Under warmer conditions refer to thinning advice.
- Stir thoroughly before and during application.
- Apply 2 coats by brush, roller or spray.
- All times quoted assume ambient conditions of 25°C and 50% relative humidity. At cooler temperature or higher humidity drying times will be extended.
- Please check the colour for accuracy before application. Haymes Paint will not be accountable for the application of incorrect colours.

### Thinning

Thinning is not recommended unless spraying; add up to 100ml clean water per litre of paint to achieve acceptable atomisation. Up to 50ml of water can be added per litre of paint to ease application under very warm conditions.

### Care and Maintenance

New paintwork should not be exposed to steam or condensation for 72 hours. Protect the coating against abrasive contact for 7 days. After 7 days the finish can be cleaned with a mild detergent solution and a soft cloth.

### Storage

Protect from extremes of temperature. Store between 5°C and 30°C.

### Safety Directions

**Keep out of reach of children.** Avoid contact with skin and eyes. Wear suitable, protective clothing, eye protection and impervious gloves when mixing and using.

### First Aid Instructions

If swallowed, drink plenty of water and seek medical advice. Contact a doctor or Poisons Information Centre (Phone 13 1126). If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water. If irritation develops or persists seek medical advice. In case of eye contact, hold eyes open and flush with running water for at least 15 minutes and seek medical advice.

**Protect our environment**

DO NOT pour any leftover product down the drain. Retain in a marked sealed container for future use or disposal via special chemical waste collection programs. Dried empty containers can be recycled and should be disposed of via recycling facilities.

**Manufacturer's comment**

This product has been designed as part of a totally integrated application system. Use with any other manufacturer's product(s) or failing to follow application instructions, could result in detrimental effects on product performance, for which Henry Haymes Pty. Ltd. cannot be held responsible. Further information is available in the form of Safety Data and Product Information Sheets from Haymes Paint (1800 033 431). We are continually updating materials and methods, so please ensure you have the latest information.

Henry Haymes Pty Ltd  
A.B.N. 14 004 201 638  
Waringa Drive  
Wendouree Industrial Estate  
Ballarat Vic 3350  
Freecall 1800 033 431  
Freefax 1800 801 892  
[www.haymepaint.com.au](http://www.haymepaint.com.au)

**Date of Preparation**            29/9/14