

OneStep™ Bond-Tite™

**Use to bond
pool plaster over
existing plaster finishes**

BONDING AGENT

ALL-IN-ONE

**65 lb NET WT
29.5 kg**

N2019-11472

#084030



8 19019 94100 2

PMM
PREMIX-MARBLETTITE®

Manufactured In The U.S.A.
Pompano Beach, FL (954) 917-7665 • Winter Springs, FL (407) 327-0830
www.PMMproducts.com

- **EASY 1 Part System**
- **Superior bonding with most cementitious surfaces**
- **Superior elongation that allows for minor movements of substrates**

8 19019 94100 2

8 19019 94100 2

8 19019 94100 2

USES

OneStep Bond-Tite is the product of choice for pool, patio, deck or sidewalk renovation. It provides superior performance as a bond coat over existing cementitious surfaces. The finish coat locks to the Bond-Tite both chemically and mechanically to reduce the possibility of bond loss, thereby reducing the need for strong acid washing, sand blasting or axing of the existing surface.

COVERAGE

Should be applied at a rate not to exceed 200-300 square feet per 65# bag. Coverage will vary depending on the porosity of the substrate.

PREPARATION

Patch, level or resurface as required to provide a smooth substrate. Surface must be clean, cool, dry and free of mold, mildew, fungus, algae, dirt, grease, paint, efflorescence or other foreign matter that may prevent or inhibit proper bonding.

NOTE: Only the experienced applicator can make the decision as to what surface preparation may be required.

1) On previously plastered pools it is necessary to grind around the tile, lights, returns, etc., to allow for a smooth transition.

2) On previously painted pools, the surface must be sandblasted to remove the old paint completely.

3) Thoroughly wash the surface with a TSP solution to remove body oils and suntan lotions. Acid wash with a 50/50 solution of muriatic acid and water, rinse with a neutralizing solution of baking soda and water, and then rinse with clean water.

MIXING

1) Pour approx 1-1/4 gallons cool potable water into a clean mixing container. Add 1 bag of **OneStep Bond-Tite Dry Mix** and thoroughly mix until a smooth lump-free consistency is achieved.

2) Allow this mix to stand for approximately 5 minutes.

3) Add up to 2 ounces of water per mixed bag to retemper the mix if necessary to achieve the desired workable consistency. Do not retemper the mix a second time.

WARNING: Only use water to retemper after mixing with Bond-Tite Dry Mix.

APPLICATION

Apply the **OneStep Bond-Tite** with a 1-1/4" nap roller. Recommended thickness of application is between 1/8" to 3/16".

Allow **OneStep Bond-Tite** to thoroughly dry for a minimum of 24 hours before coating. If temperatures are below 50°F or wet conditions such as fog, high humidity or rain exist, the drying times will be significantly extended.

CLEAN UP

Clean all tools and equipment with water while still wet. Cured material can be removed mechanically or chemically.

STORAGE

Turn inventory regularly and keep bagged product protected from all forms of moisture, both direct and indirect, to assure maximum product usage, uniformity and productivity.

LIMITATIONS

Apply only when surface and ambient temperatures are 50°F - 100°F and relative humidity is below 85% throughout the application and for a minimum of 24 hours thereafter or prior to replastering.

Protect **Bond-Tite** from rain, fog or other moisture after application. Moisture will prevent **Bond-Tite** from curing. Surface hardness of **Bond-Tite** is not an indication of complete cure.

WARRANTY

The effectiveness of this product depends upon its proper application and the condition and preparation of the surface to which it is applied. The product shall be in its unopened package and of the kind specified within. THERE IS NO OTHER WARRANTY OR REPRESENTATION OF ANY KIND, EXPRESS OR IMPLIED (INCLUDING NO WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE). No warranty shall be implied by law. This limited warranty continues only until such time as the buyer opens the package and examines its contents. If the buyer, after opening the package and examining its contents, determines that the product is not of the kind specified herein, the buyer should write to PREMIX-MARBLETTITE MANUFACTURING COMPANY, 1259 NW 21st Street, Pompano Beach, Florida 33069, explaining the defect and enclosing a sample of the product. PREMIX-MARBLETTITE, upon receipt of the sample from the buyer, will replace the portion of the product that is determined to be defective. This shall be the buyer's sole remedy for breach of warranty and such remedy shall be in lieu of any claim for damages, including consequential damages. Some states do not allow limitations on how long an implied warranty lasts, or exclusions or limitations of incidental or consequential damages, so the above limitations or exclusions may not apply to you. This warranty gives you specific legal rights, and you may also have other rights, which vary from state to state. The information contained in this bulletin conforms to the standard detail recommendations and specifications for the installation of the products manufactured by PREMIX-MARBLETTITE and is presented in good faith. PREMIX-MARBLETTITE assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project.

PREPARACIÓN

Realice parches, nivele o vuelva a rehacer la superficie de acuerdo a lo requerido para obtener una superficie plana. La superficie deberá estar limpia, fresca, seca y libre de moho, miliú, hongos, algas, mugre, grasa, pintura, efflorescencia, cualquier otra cosa que pudiera interferir con la adhesión apropiada.

NOTA: Solamente un instalador con experiencia podría tomar la decisión en cuanto a los requerimientos para la preparación de la superficie.

1) En las piscinas que previamente se le haya aplicado yeso, es necesario amolar alrededor de las losetas, las luces, los retornos etc., para permitir una transición lisa.

2) Las piscinas que hayan sido pintadas previamente, deberá limpiarles la superficie con chorro de arena para remover completamente la pintura vieja.

3) Limpie la superficie completamente con una solución de TSP (fostato de trisódico) para remover las grasas producidas por el cuerpo y los bronceadores. Un lavado con ácido de 50% de ácido muriático y 50% agua, enjuague con una solución neutralizante de bicarbonato de sodio y agua y después enjuague con agua limpia.

USOS

El **OneStep Bond-Tite** es el producto de elección para renovar las piscinas, los patios, las cubiertas y las aceras. Proporciona un desempeño superior como una capa adhesiva sobre las superficies cementosas preexistentes. La capa de acabado se fija con el Bond-Tite tanto de manera química como mecánica para reducir la posibilidad de perdida de la adhesión, de esa manera disminuye la necesidad de realizar un lavado con ácido, chorrear con arena o de reducción de la superficie existente.

COBERTURA

Deberá ser aplicado a un rango que no excede 18.58 m² - 27.87 m² (200-300 pies cuadrados) por bolsa de 29 kg (65 libras). La cobertura variará dependiendo de la porosidad del substrato.

PREPARACIÓN

Realice parches, nivele o vuelva a rehacer la superficie de acuerdo a lo requerido para obtener una superficie plana. La superficie deberá estar limpia, fresca, seca y libre de moho, miliú, hongos, algas, mugre, grasa, pintura, efflorescencia, cualquier otra cosa que pudiera interferir con la adhesión apropiada.

NOTA: Solamente un instalador con experiencia podría tomar la decisión en cuanto a los requerimientos para la preparación de la superficie.

1) En las piscinas que previamente se le haya aplicado yeso, es necesario amolar alrededor de las losetas, las luces, los retornos etc., para permitir una transición lisa.

2) Las piscinas que hayan sido pintadas previamente, deberá limpiarles la superficie con chorro de arena para remover completamente la pintura vieja.

3) Limpie la superficie completamente con una solución de TSP (fostato de trisódico) para remover las grasas producidas por el cuerpo y los bronceadores. Un lavado con ácido de 50% de ácido muriático y 50% agua, enjuague con una solución neutralizante de bicarbonato de sodio y agua y después enjuague con agua limpia.

PREPARACIÓN DE LA MEZCLA

1) Vierta aproximadamente 4.73 L (1 1/4 gal) de agua potable fresca en un envase limpio para mezclar. Añada 1 bolsa de mezcla seca **OneStep Bond-Tite Dry Mix** y mezcle completamente hasta que logre una consistencia libre de grumos.

2) Permita que esta mezcla reposé durante al menos 5 minutos.

3) Si es necesario, añada 57 g (2 onzas) de agua por cada bolsa mezclada, para reacondicionar la mezcla, para así lograr la consistencia deseada de trabajo. No reacondicione la mezcla una segunda vez.

ADVERTENCIA: Solamente utilice agua para reacondicionar la mezcla después de haberla mezclado con la mezcla seca **Bond-Tite Dry Mix**.

APLICACIÓN

Aplique el **OneStep Bond-Tite** a un rodillo con pelillo de 3.2 cm (1-1/4"). El grosor de aplicación recomendado es entre 0.3 cm y 0.47 cm.

Permita que el **OneStep Bond-Tite** se seque completamente durante un mínimo de 24 horas antes de recubrir. Si las temperaturas están por debajo de los 10°C (50°F) o las condiciones húmedas tales como neblina, una humedad alta o lluvia existente, los tiempos de secado deberán ser extendidos significativamente.

WARNING

This product can expose you to chemicals including Crystalline Silica, which is known to the State of California to cause cancer.

For more information go to:
P65warnings.ca.gov

CLEAN UP

several minutes. Remove contact lenses if present and easy to do – continue rinsing. If exposed or concerned: Get medical advice/attention. Store locked up. Dispose of contents/container in accordance with local authority requirements. Incineration is the preferred method of disposal.

FIRST AID: Inhalation - Move victim to fresh air. Consult physician if necessary.

Skin Contact - Wash with soap and water. Remove contaminated clothing. Consult physician if necessary. Eye Contact - Flush with copious amounts of water for at least 15 minutes occasionally lifting upper and lower eyelids. Remove any contact lenses. Consult physician if necessary. Ingestion - Do not induce vomiting. Rinse skin with water/shower. If INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. If IN EYES: Rinse continuously with water for

DANGER! HAZARDS:

PELIGRO! PELIGROS:

PRECAUCIONES:

PRIMEROS AUXILIOS:

MANTENGASE FUERA DEL ALCANCE DE LOS NIÑOS

para respirar. SI ENTRA EN CONTACTO CON LOS OJOS: Enjuague continuamente con agua durante varios minutos. Remueva los lentes de contacto si los tiene puestos y si le es fácil continúe enjuagando. En caso de exponerse o de estar preocupado: Obtenga consejos y atención médica. Almacénelo con bloqueo de seguridad. Deséche lo restante y el envase de acuerdo a los requerimientos de las autoridades locales. Incineración es el método preferido para desechar.

PRIMEROS AUXILIOS: Inhalación: Lleve a la víctima hacia el aire fresco. Consulte a un médico si es necesario. Contacto con la piel: Lave con agua y jabón. Quite la ropa contaminada. Consulte a un médico si es necesario. Contacto con los ojos: Enjuague continuamente con bastantes cantidades de agua durante al menos 15 minutos, levantando ocasionalmente los párpados de arriba y de abajo. Quite los lentes de contacto si los tiene puestos. Consulte a un médico si le es necesario. Ingestión: No induzca el vomito. Lave la boca con agua. Consulte a un médico.

MANTENGASE FUERA DEL ALCANCE DE LOS NIÑOS

