

GENERAL INFORMATION

TRIGGERFOAM™ PRO - WINDOW & DOOR

Polyurethane Expanding Foam

PRODUCT DESCRIPTION

TriggerFoam Pro is a one part polyurethane expanding foam which sets into its final form by using moisture present in the air. When installing the foam, consideration should be given to the additional expansion of the foam after it leaves the nozzle. The surface of the foam initially dries within 1-5 hours and becomes fully cured in 12-15 hours. Low pressure formula will not distort windows and door frames. TriggerFoam Pro sets well on ordinary surfaces such as concrete, brick, metal, etc. Surfaces do not require preparation and can also be damp. After installation, it is recommended that a full 24 hours elapse prior to scraping, sanding, staining or painting. The foam has a R-5 equivalent value when used in place of traditional installation methods.

TriggerFoam Pro is dispensed through a special gun that allows the user to control the rate of flow as well as the size of the bead for more precise placement of the product, allowing it to be used in a wide variety of applications. Use it to fill, seal or insulate. It blocks drafts, stops leaks, saves energy, adheres to all types of construction materials, deadens sound, acts as a buoyancy material once cured, controls radon, helps confine asbestos fibers, and can be used in HVAC applications.

GENERAL APPLICATIONS AND USES

INSULATING

- Around window frames, sills, door frames floor/wall joints
- Refrigeration units and pipes
- Electrical junction boxes
- Foundations and sill plates
- Air conditioning systems

FILLING

- Breaches in walls
- Sound Dampening
- Voids in concrete forms
- Pipe penetrations in non-fire rated walls
- Underground ductwork
- Gaps in construction materials

FEATURES AND BENEFITS

- CFC free propellant
- Class B2 Flame retardant
- Physiologically harmless when fully cured
- Contains no urea formaldehyde or PCB's
- Does not rot or deteriorate with age
- Low odor
- High foam yield – up to 1.6 ft³ per 29 oz. can
- Easily adjustable applicator can dispense foam beads as small as 1/8"
- Hardened steel dispenser tip for longer life on metal tools
- Precision valve helps prevent pressure loss and prolongs shelf life
- Stop and go application, product remains liquid in applicator until dispensed
- Minimal subsequent expansion ($\pm 10\%$)
- Compatible with PVC
- VOC: 185.5 g/L

APPROVALS AND LISTINGS

- International Code Council Evaluation Service (ICC-ES), ESR-3263 for Thermal and Moisture Protection and annular space protection for wood fire blocking. Code compliant with the 2021 IBC/IRC, 2018 IBC/IRC, 2015 IBC/IRC, and 2012 IBC/IRC.
- Underwriters Laboratory (UL Listing) – File No. R16754, Caulkings and Sealants. Tested in accordance with UL 723 (ASTM E84) "Test for Surface Burning Characteristics of Building Materials" Applied to Inorganic Reinforced Cement Board tested as applied in two 3/4" diameter beads, 5" OC covering 12.5 percent of the exposed test area: Flame spread 0, Smoke developed 10
- GEV-EMICODE EC 1 Plus very low emissions classification, License No. 16148
- Tested in accordance with ASTM E90 (Sound Transmission Classification 60)
- Tested in accordance with ASTM E814 (modified for fireblocking products)
- Tested in accordance with AAMA E812-04 for Pressure Build

SECTION CONTENTS

General Information.....	1
Technical Data	2
Installation Procedures	2
Ordering Information.....	2



TRIGGERFOAM PRO - WINDOW & DOOR

CAN SIZES

- 29 oz.

SUITABLE BASE MATERIALS

- Concrete
- Masonry
- Wood
- Metal
- Aluminum
- Steel

TECHNICAL DATA

Volume Yield	29 oz.: 2,420-3,110 in ³ or 1.4 -1.6 ft ³ (40-45 liters)
Density (Of Foamed Product)	1.00-1.12 lb/ft ³ (depending on temperature and humidity)
Tack Free Time	5-10 minutes (depending on temperature and humidity)
Cutting Time	10-15 minutes (depending on temperature and humidity)
Initial Drying Time	1-5 hours (depending on temperature and humidity)
Full Curing Time	12 -15 hours (depending on temperature and humidity)
Application Temperature	41°F (5°C) minimum for application surfaces
Temperature Resistance of Cured Product	-40°F to +195°F (-40°C to +90°C)
Compressive Strength of Cured Product	6 psi
Elongation At Breakage of Cured Product	20-30%
Closed Cell Content of Cured Product	60 to 70%
Approximate Specific Density of Cured Product	18 kg/m ³
Air Permeability of Cured Product	<0.1 m ³ /[h·m·(daPa)] ²³
Water Vapor Permeability (Resistance Factor) of Cured Product	μ = 54
Water Absorption of Cured Product	Less than 1% by volume (DIN 53428)
Contents	29 oz. (822g) Net Weight
Shelf Life	18 months 41°F to 77°F (+5°C to +25°C) (stored in vertical position) Higher temperature = shorter shelf life

INSTALLATION PROCEDURES

- Remove any dirt, dust, grease and any other loose debris from the building elements surface prior to applying TriggerFoam Pro. It is helpful to dampen the surface to enhance TriggerFoam Pro's ability to bond prior to dispensing.
- Remove the cap of the aerosol can to reveal the plastic threaded connection and valve stem. Select a TriggerFoam Gun and attach to the can by engaging the gun's matching threads and turning clockwise until tightened. Be careful not to overtighten.
- Shake can well and follow the arrows on the label indicating the direction of use. Turn the can over as suggested by the arrows. The TriggerFoam Pro Gun is now effectively at the "bottom" of the can.
- Prior to dispensing TriggerFoam Pro, open the screw located at the rear of the gun by turning counterclockwise (initially about 1/4 turn), and then pull the trigger. Adjusting the screw will control the size of the dispensed bead of foam. Varying pressure on the trigger will control the rate of flow. Caution: do not completely remove the screw at the rear of the gun while connected to a "live" can of TriggerFoam.
- It is not necessary to exhaust the entire contents of the can. When finished applying TriggerFoam Pro, the screw at the rear of the gun can be tightened to halt further flow. Do not remove the TriggerFoam Pro gun from the can. Peeling cured foam off the end of the gun's nozzle and reopening the screw allows for use of the remaining contents at a later time.
- While the application is ongoing, remove the exhausted can and immediately mount a new can of TriggerFoam Pro onto the gun while it still contains wet, uncured foam. When the job is done and the last can of TriggerFoam Pro is exhausted, immediately unscrew the gun from the can and attach a well-shaken can of TriggerFoam Pro Cleaner. Two or three quick squirts of TriggerFoam Pro Cleaner through the gun while the foam is still wet and uncured is recommended to keep the gun clean and ready for the next application. Completely emptied cans of TriggerFoam Pro can be discarded with common construction waste. Cured foam can only be removed mechanically.

ORDERING INFORMATION
TriggerFoam

Cat. No.	Description	Pack Qty.	Carton Qty.
8134P-PWR	TriggerFoam Pro Window & Door 29 fl. oz.	12	12


TriggerFoam Tools and Accessories

Cat. No.	Description	Pack Qty.	Carton Qty.
08128-PWR	TriggerFoam Pro Deluxe Metal Gun	1	10
08141-PWR	TriggerFoam Pro Brass Replacement Gun Tip	1	1


TriggerFoam

Cat. No.	Description	Pack Qty.	Carton Qty.
08147-PWR	TriggerFoam Pro Cleaner 17 fl. oz.	6	6

