

Proud Member and Participant of:

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506









Material and Performance Specification

ECC-2B™ Double Net Coconut Biodegradable Rolled Erosion Control Product

Description:

The ECC-2B™ is made with uniformly distributed 100% coconut fiber and two organic jute nets securely sewn together with biodegradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation.

The ECC-2B™ has functional longevity of approximately 24 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 1:1 and medium to high flow channels. The ECC-2B™ meets Type 4 specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Matrix:	1	2	
	100% Coconut		
Netting:	Туре		Net Color
Top: Orga	anic Leno Weave Jute		Natural
Middle: Non	e		
Bottom: Orga	anic Leno Weave Jute		
Net Opening:	Тор	Middle	Bottom
	0.5" x 1.0"		0.5" x 1.0"
Thread:	Туре	Color	
	Biodegradable Thread	Natural	
Roll Sizes:	Standard	"A" Size	Mega
Width:	8 ft 2.4 m	4 ft 1.2 m	16 ft 4.9 m
Length:	112.5 ft 34.3 m	225 ft 68.6 m	112.5 ft 34.3 m
Weight*:	60 lbs 27.2 kg	60 lbs 27.2 kg	120 lbs 54.4 kg
Area:	100 yd² 83.6 m²	100 yd² 83.6 m²	200 yd² 167.2 m²
#/Pallet:	20	6	20

^{*}Weight at time of manufacturing.

Index Value Properties*:					
Property	Test Method	Typical			
Mass/Unit Area	ASTM D6475	9.50 oz/yd ²	322.1 g/m2		
Thickness	ASTM D6525	0.23 in	5.84 mm		
Tensile Strength-MD	ASTM D6818	223 lb/ft	3.25 kN/m		
Elongation-MD	ASTM D6818	11 %			
Tensile Strength-TD	ASTM D6818	150 lb/ft	2.19 kN/m		
Elongation-TD	ASTM D6818	16.0 %			
Light Penetration	ASTM D6567	13 %			
Density / Specific Gravity	ASTM D792	N/A g/cm ³			
Water Absorption	ASTM D1117	340 %			

^{*}May differ depending upon raw material variations

esign Values*:			
Test Method ASTM D6459		Value 0.04	
0.040	0.053	0.102	
0.060	0.084	0.120	
0.094	0.114	0.134	
	Test Me ASTM Do ≤ 3:1 0.040 0.060	Test Method ASTM D6459 ≤ 3:1 3:1-2:1 0.040 0.053 0.060 0.084	

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Test Method	Parameters	Results	
	50mm (2in) / hr-30 min	SLR**=14.16	
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=18.25	
	150mm (6in) / hr-30 min	SLR**=23.24	
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.76 lb/ft ²	
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 501 %	
*Bench scale tests should not be	used for design purposes.		

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

**Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor

Property	Test Method	Value			
Unvegetated Shear Stress	ASTM D 6460	2.25	lbs/ft ²	107.73	Pa
Unvegetated Velocity	ASTM D 6460	9.0	ft/s	2.74	m/s
Vegetated Shear Stress	NA	N/A	lbs/ft ²	N/A	Pa
Vegetated Velocity	NA	N/A	ft/s	N/A	m/s
Manning's N (Value Represents a Range)			0.02	25	

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory