

Proud Member and Participant of:

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506









Material and Performance Specification

ECS-1B™ Single Net Straw Biodegradable Rolled Erosion Control Product

Description:

The ECS-1B™ is made with uniformly distributed 100% agricultural straw and one organic jute net securely sewn together with biodegradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation.

The ECS-1B™ has functional longevity of approximately 12 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 3:1 or less and low flow channels. The ECS-1B™ meets Type 2.C specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Matrix:	1	2	
	100% Straw		
Netting:	Туре		Net Color
Top:	Organic Leno Weave Jute		Natural
Middle:	None		
Bottom:	None		
Net Opening:	Тор	Middle	Bottom
	0.5" x 1.0"		
Thread:	Туре	Color	
	Biodegradable Thread	Natural	
Roll Sizes:	Standard	"A" Size	Mega
Width:	8 ft 2.4 m	4 ft 1.2 m	16 ft 4.9 m
Length:	112.5 ft 34.3 m	225 ft 68.6 m	112.5 ft 34.3 m
Weight*:	57 lbs 25.9 kg	57 lbs 25.9 kg	114 lbs 51.7 kg
Area:	100 yd² 83.6 m²	100 yd² 83.6 m²	200 yd² 167.2 m²
#/Pallet:	20	6	20

^{*}Weight at time of manufacturing.

Index Value Properties	*:	
Property	Test Method	Typical
Mass/Unit Area	ASTM D6475	9.00 oz/yd² 305.1 g/m2
Thickness	ASTM D6525	0.30 in 7.62 mm
Tensile Strength-MD	ASTM D6818	106 lb/ft 1.55 kN/m
Elongation-MD	ASTM D6818	17 %
Tensile Strength-TD	ASTM D6818	118 lb/ft 1.72 kN/m
Elongation-TD	ASTM D6818	26.8 %
Light Penetration	ASTM D6567	20 %
Density / Specific Gravity	ASTM D792	N/A g/cm ³
Water Absorption	ASTM D1117	492 %

^{*}May differ depending upon raw material variations

Slope Performance Design Values*:						
Property Test Method C-Factors ASTM D6459		Value				
		0.08				
≤ 3:1	3:1-2:1	≥ 2:1				
0.075	N/A	N/A				
0.156	N/A	N/A				
0.236	N/A	N/A				
	Test Me ASTM D ≤ 3:1 0.075 0.156	Test Method ASTM D6459 ≤ 3:1 3:1-2:1 0.075 N/A 0.156 N/A				

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Bench-Scale Testing* (NTPEP***):				
Test Method	Parameters	Results		
	50mm (2in) / hr-30 min	SLR**=6.73		
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=7.45		
	150mm (6in) / hr-30 min	SLR**=8.26		
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	1.40 lb/ft ²		
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 580 %		
*Bench scale tests should not be	used for design purposes.			
**Soil Loss Ratio=Soil Loss Bare S	oil/Soil Loss with RECP=1/C-	Factor		
***The preceding test data excer	nts were reproduced with t	he nermission		

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Test Method	Value			
ASTM D 6460	1.55	lbs/ft ²	74.21	Pa
ASTM D 6460	6.8	ft/s	2.07	m/s
NA	N/A	lbs/ft ²	N/A	Pa
NA	N/A	ft/s	N/A	m/s
	ASTM D 6460 ASTM D 6460 NA	ASTM D 6460 1.55 ASTM D 6460 6.8 NA N/A	ASTM D 6460 1.55 lbs/ft ² ASTM D 6460 6.8 ft/s NA N/A lbs/ft ²	ASTM D 6460 1.55 lbs/ft² 74.21 ASTM D 6460 6.8 ft/s 2.07 NA N/A lbs/ft² N/A

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory