

Proud Member and Participant of:

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506









Material and Performance Specification

ECS-1D™ Temporary Single Net Straw Rolled Erosion Control Product

Description:

The ECS-1D™ is made with uniformly distributed 100% agricultural straw and one polypropylene net securely sewn together with degradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation.

The ECS-1D™ has functional longevity of approximately 45 to 90 days, but will vary depending on soil and climatic conditions, and is suitable for slopes 3:1 or less. The ECS-1D™ meets Type 1.C specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Matrix:	1	2		
	100% Straw			
Netting:	Туре		Net Color	
Top: Acce	lerated Lightweight Photodegradable I	Polypropylene	Clear - 1% UVD	
Middle: Non	e			
Bottom: Non-	е			
Net Opening:	Тор	Middle	Bottom	
	0.5" x 0.5"			
Thread:	Туре	Color		
	Degradable Thread	White		
Roll Sizes:	Standard	"A" Size	Mega	
Width:	8 ft 2.4 m	4 ft 1.2 m	16 ft 4.9 m	
Length:	112.5 ft 34.3 m	225 ft 68.6 m	112.5 ft 34.3 m	
Weight*:	50 lbs 22.7 kg	50 lbs 22.7 kg	100 lbs 45.4 kg	
Area:	100 yd² 83.6 m²	100 yd² 83.6 m²	200 yd² 167.2 m²	
#/Pallet:	25	9	25	

^{*}Weight at time of manufacturing.

Index Value Properties*:					
Property	Test Method	Typical			
Mass/Unit Area	ASTM D6475	8.00 oz/yd ² 271.2 g/m2			
Thickness	ASTM D6525	0.30 in 7.62 mm			
Tensile Strength-MD	ASTM D6818	121 lb/ft 1.77 kN/m			
Elongation-MD	ASTM D6818	30 %			
Tensile Strength-TD	ASTM D6818	79 lb/ft 1.15 kN/m			
Elongation-TD	ASTM D6818	35.0 %			
Light Penetration	ASTM D6567	22 %			
Density / Specific Gravity	ASTM D792	N/A g/cm ³			
Water Absorption	ASTM D1117	458 %			

^{*}May differ depending upon raw material variations

sign Values*:			
Test Me	thod	Value	
ASTM D6459		0.02	
≤ 3:1	3:1-2:1	≥ 2:1	
0.024	N/A	N/A	
0.105	N/A	N/A	
0.185	N/A	N/A	
	Test Me ASTM D ≤ 3:1 0.024 0.105	Test Method ASTM D6459 ≤ 3:1 3:1-2:1 0.024 N/A 0.105 N/A	

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Test Method	Parameters	Results	
	50mm (2in) / hr-30 min	SLR**=6.29	
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=5.80	
	150mm (6in) / hr-30 min	SLR**=5.37	
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	1.10 lb/ft ²	
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 517 %	
*Bench scale tests should not be a	used for design purposes.		
**Soil Loss Ratio=Soil Loss Bare So	oil/Soil Loss with RECP=1/C-	Factor	

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Channel Performance Design Values*:						
Property	Test Method	Value				
Unvegetated Shear Stress	ASTM D 6460	1.50	lbs/ft ²	71.82	Pa	
Unvegetated Velocity	ASTM D 6460	6.8	ft/s	2.07	m/s	
Vegetated Shear Stress	NA	N/A	lbs/ft ²	N/A	Pa	
Vegetated Velocity	NA	N/A	ft/s	N/A	m/s	
Manning's N (Value Represents a Range)			0.02	25		

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory