

Proud Member and Participant of:

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506









Material and Performance Specification

ECS-2D™ Temporary Double Net Straw Rolled Erosion Control Product

Description:

The ECS-2D™ is made with uniformly distributed 100% agricultural straw and two polypropylene nets securely sewn together with degradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation.

The ECS-2D™ has functional longevity of approximately 45 to 90 days, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 to 3:1 and low to medium flow channels. The ECS-2D™ meets Type 1.D specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Matrix:		1		2					
	10	00% Straw							
Netting:		Туре				Net (Color		
Top: Accelerated Lightweight Photodegradable Polypropylene			dable Polypropylene			Clear - 1	Clear - 1% UVD		
Middle:	: None								
Bottom:	: Accelerated Lightwei	ight Photodegra	dable Polypropylene						
Net Opening:		Тор		Mid	dle	Bot	Bottom		
	C).5" x 0.5"				0.5"	(0.5"		
Thread:	Туре			Color					
	Degradable Thread			White					
Roll Sizes:		Standard		"A" S	ize	Me	ga		
Width:	: 8 ft	2.4 m	4	ft	1.2 m	16 ft	4.9 m		
Length:	: 112.5 ft	34.3 m	225	ft	68.6 m	112.5 ft	34.3 m		
Weight*:	53 lbs	24.0 kg	53	lbs	24.0 kg	106 lbs	48.1 kg		
Area:	: 100 yd	2 83.6 m ²	100	yd²	83.6 m ²	200 yd ²	167.2 m ²		
#/Pallet:		25		9		2	5		

^{*}Weight at time of manufacturing.

Index Value Properties*:					
Property	Test Method	Typical			
Mass/Unit Area	ASTM D6475	8.50 oz/yd² 288.2 g/m2			
Thickness	ASTM D6525	0.32 in 8.13 mm			
Tensile Strength-MD	ASTM D6818	169 lb/ft 2.47 kN/m			
Elongation-MD	ASTM D6818	28 %			
Tensile Strength-TD	ASTM D6818	107 lb/ft 1.56 kN/m			
Elongation-TD	ASTM D6818	29.4 %			
Light Penetration	ASTM D6567	19 %			
Density / Specific Gravity	ASTM D792	N/A g/cm ³			
Water Absorption	ASTM D1117	368 %			

^{*}May differ depending upon raw material variations

Value
0.01
1 ≥ 2:1
N/A
N/A
N/A

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Test Method	Parameters	Results	
	50mm (2in) / hr-30 min	SLR**=7.89	
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=8.83	
	150mm (6in) / hr-30 min	SLR**=9.90	
ECTC Method 3 Shear Resistan	ce Shear at .50 in soil loss	1.50 lb/ft ²	
ECTC Method 4 Germination	Top soil; Fescue; 21 day incul	oation 542 %	
*Bench scale tests should not b	e used for design purposes.		

^{**}Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Channel Performance Design Values*:						
Property	Test Method	Value				
Unvegetated Shear Stress	ASTM D 6460	2.05	lbs/ft ²	98.15	Pa	
Unvegetated Velocity	ASTM D 6460	7.5	ft/s	2.29	m/s	
Vegetated Shear Stress	NA	N/A	lbs/ft ²	N/A	Pa	
Vegetated Velocity	NA	N/A	ft/s	N/A	m/s	
Manning's N (Value Represents a Range)			0.02	29		

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory