

## **Proud Member and Participant of:**

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506









## **Material and Performance Specification**

## ECSC-2B™ Double Net Straw/Coconut Biodegradable Rolled Erosion Control Product

## **Description:**

The ECSC-2B™ is made with uniformly distributed 70% agricultural straw, 30% coconut fiber and two organic jute nets securely sewn together with biodegradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECSC-2B™ has functional longevity of approximately 18 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 to 1:1 and low to medium flow channels. The ECSC-2B™ meets Type 3.B specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Matrix:	1	2	
	70% Strav	30% Coconut	
Netting:	Туре		Net Color
Top: Orga	nic Leno Weave Jute		Natural
Middle: None	9		
Bottom: Orga	nic Leno Weave Jute		
Net Opening:	Тор	Middle	Bottom
	0.5" x 1.0		0.5" x 1.0"
Thread:	Туре	Color	
	Biodegradable Th	ead Natural	
Roll Sizes:	Standar	"A" Size	Mega
Width:	8 ft 2.4	m 4 ft 1.2 m	16 ft 4.9 m
Length:	112.5 ft 34.3	m 225 ft 68.6 m	112.5 ft 34.3 m
Weight*:	60 lbs 27.2	kg 60 lbs 27.2 kg	120 lbs 54.4 kg
Area:	100 yd <sup>2</sup> 83.6	m <sup>2</sup> 100 yd <sup>2</sup> 83.6 m <sup>2</sup>	200 yd² 167.2 m²
#/Pallet:	20	6	20

<sup>\*</sup>Weight at time of manufacturing.

Index Value Properties*:					
Property	Test Method	Typical			
Mass/Unit Area	ASTM D6475	9.00 oz/yd²	305.1 g/m2		
Thickness	ASTM D6525	0.28 in	7.11 mm		
Tensile Strength-MD	ASTM D6818	204 lb/ft	2.98 kN/m		
Elongation-MD	ASTM D6818	14 %			
Tensile Strength-TD	ASTM D6818	134 lb/ft	1.96 kN/m		
Elongation-TD	ASTM D6818	16.3 %			
Light Penetration	ASTM D6567	12 %			
Density / Specific Gravity	ASTM D792	N/A g/cm <sup>3</sup>			
Water Absorption	ASTM D1117	361 %			

<sup>\*</sup>May differ depending upon raw material variations

sign Values*:			
Test Me	Test Method		
ASTM D6459		0.06	
≤ 3:1	3:1-2:1	≥ 2:1	
0.055	0.070	0.122	
0.073	0.101	0.167	
0.122	0.132	0.212	
	Test Me  ASTM Di  ≤ 3:1  0.055  0.073	Test Method  ASTM D6459  ≤ 3:1 3:1-2:1  0.055 0.070  0.073 0.101	

<sup>\*</sup>Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Bench-Scale Testing* (NTPEP***):			
Test Method	Parameters	Results	
	50mm (2in) / hr-30 min	SLR**=11.89	
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=13.60	
	150mm (6in) / hr-30 min SLR**=15	SLR**=15.50	
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.46 lb/ft <sup>2</sup>	
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 671 %	
*Bench scale tests should not be	used for design purposes.		
**Soil Loss Ratio=Soil Loss Bare S	oil/Soil Loss with RECP=1/C-	-Factor	
***The preceding test data excer of AASHTO, however, this does no			

Channel Performance Design Values*:						
Property	Test Method		Value			
Unvegetated Shear Stress	ASTM D 6460	2.00	lbs/ft <sup>2</sup>	95.76	Pa	
Unvegetated Velocity	ASTM D 6460	8.0	ft/s	2.44	m/s	
Vegetated Shear Stress	NA	N/A	lbs/ft <sup>2</sup>	N/A	Pa	
Vegetated Velocity	NA	N/A	ft/s	N/A	m/s	
Manning's N (Value Represe	ents a Range)		0.02	29		

the product, material or device by AASHTO

<sup>\*</sup>Large-Scale Results obtained by 3<sup>rd</sup> Party GAI Accredited Independent