

Proud Member and Participant of:

www.eastcoasterosion.com

443 Bricker Road Bernville, PA 19506









Material and Performance Specification

ECX-1™ Single Net Excelsior Rolled Erosion Control Product

Description:

The ECX-1™ is made with uniformly distributed 100% Aspen wood excelsior and one polypropylene net securely sewn together with degradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation.

The ECX-1™ has functional longevity of approximately 12 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 2:1 to 3:1 and low to medium flow channels. The ECX-1™ meets Type 2.C specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

Matrix:		1		2			
	Aspen W	ood Excelsior					
Netting:	Туре				Net C	Net Color	
Top:	Top: Lightweight Photodegradable Polypropylene		ne		Gre	Green	
Middle:	None						
Bottom:	None						
Net Opening:	ing: Top			Middle	Bott	Bottom	
	0.5	5" x 0.5"					
Thread:		Туре		Color			
	Degradab	ole Thread		White			
Roll Sizes:	Sta	andard	ti.	'A" Size	Me	ga	
Width:	8 ft	2.4 m	4 f	t 1.2 m	16 ft	4.9 m	
Length:	112.5 ft	34.3 m	225 f	t 68.6 m	112.5 ft	34.3 m	
Weight*:	62 lbs	28.1 kg	62 I	bs 28.1 kg	124 lbs	56.2 kg	
Area:	100 yd²	83.6 m ²	100 y	/d² 83.6 m²	200 yd ²	167.2 m ²	
#/Pallet:		20		9	20)	

^{*}Weight at time of manufacturing.

Index Value Properties*:					
Property	Test Method	Ту	pical		
Mass/Unit Area	ASTM D6475	8.80 oz/yd ²	298.4 g/m2		
Thickness	ASTM D6525	0.38 in	9.65 mm		
Tensile Strength-MD	ASTM D6818	122 lb/ft	1.78 kN/m		
Elongation-MD	ASTM D6818	33 %			
Tensile Strength-TD	ASTM D6818	86 lb/ft	1.26 kN/m		
Elongation-TD	ASTM D6818	33.0 %			
Light Penetration	ASTM D6567	36 %			
Density / Specific Gravity	ASTM D792	N/A g/cm ³			
Water Absorption	ASTM D1117	184 %			

^{*}May differ depending upon raw material variations

esign Values*:		
Test Me	thod	Value
ASTM D	0.03	
≤ 3:1	3:1-2:1	≥ 2:1
0.034	0.180	N/A
0.104	0.202	N/A
0.208	0.319	N/A
	ASTM Do ≤ 3:1 0.034 0.104	Test Method ASTM D6459 ≤ 3:1 3:1-2:1 0.034 0.180 0.104 0.202

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Bench-Scale Testing* (NTPEP***):				
Test Method	Parameters	Results		
	50mm (2in) / hr-30 min	SLR**=3.98		
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=3.64		
	150mm (6in) / hr-30 min	SLR**=3.33		
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	1.72 lb/ft ²		
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 519 %		
*Bench scale tests should not be	used for design purposes.			
**Soil Loss Ratio=Soil Loss Bare So	oil/Soil Loss with RECP=1/C-	Factor		

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Property	Test Method	Value			
Unvegetated Shear Stress	ASTM D 6460	1.78	lbs/ft ²	85.23	Pa
Unvegetated Velocity	ASTM D 6460	8.5	ft/s	2.59	m/s
Vegetated Shear Stress	NA	N/A	lbs/ft ²	N/A	Pa
Vegetated Velocity	NA	N/A	ft/s	N/A	m/s

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory