

Woven Filter Fabric

Series: Woven Paver Base Fabric

Recommended Applications: Stabilization Below Pavers

Fabric Property	Test Method	Units	Minimum Average Roll Value
Grab Tensile Strength	ASTM D 4632	lbs./ft	350 x 200
Grab Elongation	ASTM D 4632	%	15 x 15
Trapezoidal Tear	ASTM D 4533	lbs./ft	100 x 70
CBR Puncture	ASTM D 6241	lbs./ft	800
Percent Open Area	CEO-02215	%	6
Permittivity	ASTM D 4491	sec ⁻¹	.5
Permeability	ASTM D 4491	cm/sec	.14
AOS	ASTM D 4751	US Sieve	40
Water Flow	ASTM D 4491	gpm/ft ²	60
UV Resistance	ASTM D 4355	% Strength Retained @500 hours	90
Roll Size		L x W ft (sy)	12x300 6x300

Values provided represent expected values at time of manufacture. This document provides the characteristic properties of the product described.

To the best of our knowledge, the information contained herein is accurate. However, Eastgate Supply cannot anticipate all conditions under which the above product information and the products which we distribute or the products of other distributors or manufacturers in combination with the products which we offer, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of the products we distribute either alone or in combination with other products. Final determination of the suitability of any information or material for the used contemplated, or its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.

Please note: Eastgate Supply is a distributor of geotextile fabric, not the manufacturer. We source material from a number of different United States based geotextile manufacturers.