



GEOTEX® 104F is a woven monofilament polypropylene geotextile and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The individual filaments are woven into a regular network and calendared such that the filaments retain dimensional stability relative to each other. These characteristics make GEOTEX® 104F ideal for filtration applications beneath hard armor systems. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

GEOTEX® 104F conforms to the property values listed below<sup>1</sup>. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). This product is NTPEP tested for AASHTO standards.

		MARV <sup>2</sup>	
PROPERTY	TEST METHOD	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured		100%	100%
MECHANICAL			
Grab Tensile Strength	ASTM D-4632	370 x 250 lbs	1646 x 1112 N
Grab Elongation	ASTM D-4632	15 x 15 %	15 x 15 %
CBR Puncture	ASTM D-6241	950 lbs	4226 N
Trapezoidal Tear	ASTM D-4533	100 x 60 lbs	445 x 267 N
ENDURANCE			
UV Resistance at 500 hrs	ASTM D-4355	90%	90%
HYDRAULIC		-	
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	70 US Std. Sieve	0.212 mm
Percent Open Area	CW-02215 MOD. <sup>4</sup>	4%	4%
Permittivity	ASTM D-4491	0.28 sec <sup>-1</sup>	0.28 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	18 gpm/ft²	733 l/min/m <sup>2</sup>
ROLL SIZES <sup>5</sup>		6 ft x 300 ft	1.83 m x 91.5 m
INOLE SIZES		12 ft x 300 ft	3.66 m x 91.5 m

## NOTES:

- 1. The property values listed above are effective 12/17/2018 and are subject to change without notice.
- 2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported. Values represent testing at time of manufacture.
- 3. Maximum average roll value.
- 4. Army Corp of Engineers test method correlated to light emitted through fabric. (Area of Openings/Total Area X 100%)
- 5. Contact your local Territory Business Manager (TBM) for custom widths and colors. Lead times may vary depending on customer requirements and volume requested.



ENGINEERED EARTH SOLUTIONS<sup>TM</sup>

www.propexglobal.com

Propex Operating Company, LLC · 4019 Industry Drive Chattanooga, TN 37416 · ph 800 621 1273 · ph 423 855 1466

 $ARMORMAX^{@}, PYRAMAT^{@}, LANDLOK^{@}, X3^{@}, PYRAWALL^{@}, SCOURLOK^{@}, GEOTEX^{@}, PETROMAT^{@}, PETROTAC^{@}, REFLECTEX^{@}, and GRIDPRO^{TM} are registered trademarks of Propex Operating Company, LLC.$ 

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.