

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

SHIELDskin CHEM* NEO NITRILE* 300



0120

EN374:2003



LEVEL 3

EN374:2003




AJ, KL

EN388:2003



3000



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal & irreversible risks
- Powder-free red/white polychloroprene/nitrile glove
- twinSHIELD* double-walled protection
- Ambidextrous
- 300 mm / 0.25 mm (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Good chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Type I hypersensitivity eliminated - Type IV hypersensitivity reduced

SHIELDskin* ORANGE NITRILE* 260



0120

EN374:2003



LEVEL 3

EN374:2003



[?]



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal and irreversible risks
- Powder-free orange/white nitrile/polychloroprene glove
- twinSHIELD* double-walled protection
- Ambidextrous
- 260 mm / 0.14 mm (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Tested according to EN 1149-1-2-3 & 5
- Type I hypersensitivity eliminated - Type IV hypersensitivity reduced
- Accelerator free

ecoSHIELD* Eco Nitrile PF 250



0120

EN374:2003




LEVEL 3

EN374:2003



[?]



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal and irreversible risks
- Powder-free green/white nitrile glove
- twinSHIELD* double-walled protection
- Ambidextrous
- 250 mm / 0.10 mm (XL/10: 260 mm) (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Type I hypersensitivity eliminated - Type IV hypersensitivity reduced

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

64-19-7 Acetic Acid 100%	LEVEL 3 90 min	64-19-7 Acetic Acid 100%	LEVEL 0 7 min	64-19-7 Acetic Acid 100%	LEVEL 0 4 min
108-24-7 Acetic anhydride	LEVEL 1 21 min	108-24-7 Acetic anhydride	Not Tested	108-24-7 Acetic anhydride	Not Tested
67-64-1 Acetone 99,8%	LEVEL 0 7 min	67-64-1 Acetone 99,8%	LEVEL 0 1 min	67-64-1 Acetone 99,8%	LEVEL 0 0 min
75-05-8 Acetonitrile 99,9%	LEVEL 1 20 min	75-05-8 Acetonitrile 99,9%	LEVEL 0 0 min	75-05-8 Acetonitrile 99,9%	LEVEL 0 0 min
10127-02-3 Acridine orange	LEVEL 6 480 min	10127-02-3 Acridine orange	LEVEL 6 480 min	10127-02-3 Acridine orange	LEVEL 6 480 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min	79-06-1 Acrylamide 40%	LEVEL 6 480 min	79-06-1 Acrylamide 40%	LEVEL 6 480 min
79-10-7 Acrylic acid 99%	LEVEL 2 47 min	79-10-7 Acrylic acid 99%	LEVEL 0 4 min	79-10-7 Acrylic acid 99%	Not Tested
107-13-1 Acrylonitrile 99%	Not Tested	107-13-1 Acrylonitrile 99%	LEVEL 0 0 min	107-13-1 Acrylonitrile 99%	LEVEL 0 0 min
1336-21-6 Ammonium Hydroxide 25%	Not Tested	1336-21-6 Ammonium Hydroxide 25%	LEVEL 2 31 min	1336-21-6 Ammonium Hydroxide 25%	LEVEL 1 16 min
1336-21-6 Ammonium hydroxide, 28-30%	LEVEL 4 153 min	1336-21-6 Ammonium hydroxide, 28-30%	Not Tested	1336-21-6 Ammonium hydroxide, 28-30%	Not Tested
62-53-3 Aniline 99,9%	LEVEL 2 46 min	62-53-3 Aniline 99,9%	LEVEL 1 10 min	62-53-3 Aniline 99,9%	LEVEL 1 10 min
8007-56-5 Aqua regia	LEVEL 6 480 min	Mixed Solution Aqua regia	LEVEL 6 480 min	8007-56-5 Aqua regia	Not Tested
Mixed Solution Bacillol AF	Not Tested	Mixed Solution Bacillol AF	LEVEL 2 50 min	Mixed Solution Bacillol AF	LEVEL 1 22 min
Mixed Solution Bacillol 30 Foam	Not Tested	Mixed Solution Bacillol 30 Foam	LEVEL 3 73 min	Mixed Solution Bacillol 30 Foam	LEVEL 2 48 min
71-43-2 Benzene 99%	LEVEL 0 5 min	71-43-2 Benzene 99%	Not Tested	71-43-2 Benzene 99%	Not Tested

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

98-11-3 Benzenesulfonic acid 20% solution in water	LEVEL 6 480 min	98-11-3 Benzenesulfonic acid 20% solution in water	Not Tested	98-11-3 Benzenesulfonic acid 20% solution in water	Not Tested
100-51-6 Benzyl Alcohol	LEVEL 4 123 min	100-51-6 Benzyl Alcohol	LEVEL 1 10 min	100-51-6 Benzyl Alcohol	Not Tested
7726-95-6 Bromine	LEVEL 0 7 min	7726-95-6 Bromine	LEVEL 0 6 min	7726-95-6 Bromine	Not Tested
79-08-3 Bromoacetic acid 7.5%	Not Tested	79-08-3 Bromoacetic acid 7.5%	LEVEL 4 209 min	79-08-3 Bromoacetic acid 7.5%	Not Tested
74-97-5 Bromochloromethane	Not Tested	74-97-5 Bromochloromethane	LEVEL 3 74 min	74-97-5 Bromochloromethane	Not Tested
71-36-3 Butanol 99,4%	LEVEL 5 448 min	71-36-3 Butanol 99,4%	Not Tested	71-36-3 Butanol 99,4%	LEVEL 1 25 min
71-36-3 Butanol 100%	Not Tested	71-36-3 Butanol 100%	LEVEL 2 44 min	71-36-3 Butanol 100%	Not Tested
111-76-2 2-Butoxyethanol 99%	LEVEL 4 134 min	111-76-2 2-Butoxyethanol 99%	LEVEL 1 23 min	111-76-2 2-Butoxyethanol 99%	Not Tested
97-88-1 Butyl methacrylate 99,9%	LEVEL 1 22 min	97-88-1 Butyl methacrylate 99,9%	LEVEL 1 10 min	97-88-1 Butyl methacrylate 99,9%	LEVEL 1 10 min
75-15-0 Carbon Disulfide 99,9%	LEVEL 0 1 min	75-15-0 Carbon Disulfide 99,9%	LEVEL 0 0 min	75-15-0 Carbon Disulfide 99,9%	LEVEL 0 0 min
56-23-5 Carbon Tetrachloride	LEVEL 1 12 min	56-23-5 Carbon Tetrachloride	Not Tested	56-23-5 Carbon Tetrachloride	Not Tested
Mixed Solution Chemosil 225	LEVEL 1 11 min	Mixed Solution Chemosil 225	Not Tested	Mixed Solution Chemosil 225	Not Tested
Mixed Solution Chemosil 211	LEVEL 1 14 min	Mixed Solution Chemosil 211	Not Tested	Mixed Solution Chemosil 211	Not Tested
79-11-8 Chloroacetic acid 80%	LEVEL 5 260 min	79-11-8 Chloroacetic acid 80%	LEVEL 3 75 min	79-11-8 Chloroacetic acid 80%	Not Tested
67-66-3 Chloroform 99,8%	LEVEL 0 4 min	67-66-3 Chloroform 99,8%	LEVEL 0 0 min	67-66-3 Chloroform 99,8%	LEVEL 0 0 min

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

77-92-9 Citric acid 30%	LEVEL 6 480 min	77-92-9 Citric acid 30%	LEVEL 6 480 min	77-92-9 Citric acid 30%	Not Tested
548-62-9 Crystal violet	LEVEL 6 480 min	548-62-9 Crystal violet	LEVEL 6 480 min	548-62-9 Crystal violet	Not Tested
110-82-7 Cyclohexane	LEVEL 6 480 min	110-82-7 Cyclohexane	LEVEL 6 480 min	110-82-7 Cyclohexane	LEVEL 6 480 min
108-94-1 Cyclohexanone 99%	LEVEL 1 24 min	108-94-1 Cyclohexanone 99%	LEVEL 0 5 min	108-94-1 Cyclohexanone 99%	Not Tested
66-81-9 Cycloheximide	LEVEL 6 480 min	66-81-9 Cycloheximide	LEVEL 6 480 min	66-81-9 Cycloheximide	LEVEL 6 480 min
91-95-2 Diaminobenzidine	LEVEL 6 480 min	91-95-2 Diaminobenzidine	LEVEL 6 480 min	91-95-2 Diaminobenzidine	Not Tested
79-43-6 Dichloroacetic acid 99%	LEVEL 3 80 min	79-43-6 Dichloroacetic acid 99%	Not Tested	79-43-6 Dichloroacetic acid 99%	Not Tested
107-06-2 1,2-Dichloroethane 99%	LEVEL 0 5 min	107-06-2 1,2-Dichloroethane 99%	LEVEL 0 2 min	107-06-2 1,2-Dichloroethane 99%	Not Tested
75-09-2 Dichloromethane 99%	LEVEL 0 2 min	75-09-2 Dichloromethane 99%	LEVEL 0 0 min	75-09-2 Dichloromethane 99%	LEVEL 0 0 min
68334-30-5 Diesel fuel	LEVEL 5 304 min	68334-30-5 Diesel fuel	Not Tested	68334-30-5 Diesel fuel	Not Tested
109-89-7 Diethylamine 99,5%	LEVEL 0 3 min	109-89-7 Diethylamine 99,5%	LEVEL 0 1 min	109-89-7 Diethylamine 99,5%	LEVEL 0 0 min
111-96-6 Diethylene glycol dimethyl ether 99%	LEVEL 1 19 min DR 81%	111-96-6 Diethylene glycol dimethyl ether 99%	Not Tested	111-96-6 Diethylene glycol dimethyl ether 99%	Not Tested
60-29-7 Diethyl ether 99%	LEVEL 0 6 min	60-29-7 Diethyl ether 99%	LEVEL 0 2 min	60-29-7 Diethyl ether 99%	LEVEL 0 0 min
108-20-3 Diisopropyl Ether 99%	LEVEL 1 29 min	108-20-3 Diisopropyl Ether 99%	Not Tested	108-20-3 Diisopropyl Ether 99%	Not Tested
108-20-3 Diisopropyl Ether 99%	Not Tested	108-20-3 Diisopropyl Ether 99%	LEVEL 1 16 min	108-20-3 Diisopropyl Ether 99%	Not Tested

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

7087-68-5 Diisopropyl Ethylamine 99%	LEVEL 5 322 min	7087-68-5 Diisopropyl Ethylamine 99%	Not Tested	7087-68-5 Diisopropyl Ethylamine 99%	Not Tested
127-19-5 Dimethyl Acetamide 99%	LEVEL 1 14 min	127-19-5 Dimethyl Acetamide 99%	LEVEL 0 8 min	127-19-5 Dimethyl Acetamide 99%	Not Tested
616-38-6 Dimethyl carbonate 99%	LEVEL 1 13 min	616-38-6 Dimethyl carbonate 99%	Not Tested	616-38-6 Dimethyl carbonate 99%	Not Tested
68-12-2 Dimethyl Formamide 99%	LEVEL 0 9 min	68-12-2 Dimethyl Formamide 99%	LEVEL 0 4 min	68-12-2 Dimethyl Formamide 99%	LEVEL 0 1 min
67-68-5 Dimethyl Sulfoxide 99% (DMSO)	LEVEL 4 179 min	67-68-5 Dimethyl Sulfoxide 99% (DMSO)	LEVEL 2 48 min	67-68-5 Dimethyl Sulfoxide 99% (DMSO)	LEVEL 1 10 min
123-91-1 Dioxane 99%	LEVEL 1 10 min	123-91-1 Dioxane 99%	LEVEL 0 4 min	123-91-1 Dioxane 99%	Not Tested
64-17-5 Ethanol 99.8%	LEVEL 4 154 min	64-17-5 Ethanol 99.8%	LEVEL 1 20 min	64-17-5 Ethanol 99.8%	LEVEL 0 9 min
64-17-5 Ethanol 70%	Not Tested	64-17-5 Ethanol 70%	LEVEL 2 34 min	64-17-5 Ethanol 70%	LEVEL 2 31 min
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min	1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min	1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
141-78-6 Ethyl Acetate 99.8%	LEVEL 0 5 min	141-78-6 Ethyl Acetate 99.8%	LEVEL 0 0 min	141-78-6 Ethyl Acetate 99.8%	LEVEL 0 0 min
107-15-3 Ethylene diamine 99%	LEVEL 2 50 min	107-15-3 Ethylene diamine 99%	Not Tested	107-15-3 Ethylene diamine 99%	Not Tested
107-21-1 Ethylene Glycol	Not Tested	107-21-1 Ethylene Glycol	LEVEL 0 0 min	107-21-1 Ethylene Glycol	Not Tested
Mixed Solution Euro 95 unleaded petrol	LEVEL 1 16 min	Mixed Solution Euro 95 unleaded petrol	LEVEL 1 10 min	Mixed Solution Euro 95 unleaded petrol	Not Tested
314-13-6 Evans blue	LEVEL 6 480 min	314-13-6 Evans blue	LEVEL 6 480 min	314-13-6 Evans blue	Not Tested
50-00-0 Formaldehyde 10%	LEVEL 6 480 min	50-00-0 Formaldehyde 10%	LEVEL 6 480 min	50-00-0 Formaldehyde 10%	Not Tested

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

50-00-0 Formaldehyde 37%	LEVEL 6 480 min	50-00-0 Formaldehyde 37%	LEVEL 3 87 min	50-00-0 Formaldehyde 37%	LEVEL 3 87 min DR 25%
75-12-7 Formamide 99%	Not Tested	75-12-7 Formamide 99%	LEVEL 3 99 min	75-12-7 Formamide 99%	LEVEL 1 11 min
64-18-6 Formic acid 98,5%	LEVEL 4 125 min	64-18-6 Formic acid 98,5%	LEVEL 0 4 min	64-18-6 Formic acid 98,5%	LEVEL 0 0 min
64-18-6 Formic acid 97.8%	Not Tested	64-18-6 Formic acid 97.8%	Not Tested	64-18-6 Formic acid 97.8%	LEVEL 0 3 min
111-30-8 Glutaraldehyde 25%	LEVEL 6 480 min	111-30-8 Glutaraldehyde 25%	LEVEL 6 480 min	111-30-8 Glutaraldehyde 25%	Not Tested
111-30-8 Glutaraldehyde 2.5%	LEVEL 6 480 min	111-30-8 Glutaraldehyde 2.5%	LEVEL 6 480 min	111-30-8 Glutaraldehyde 2.5%	Not Tested
50-01-1 Guanidine Hydrochloride	LEVEL 6 480 min	50-01-1 Guanidine Hydrochloride	LEVEL 6 480 min	50-01-1 Guanidine Hydrochloride	Not Tested
999-97-3 Hexamethyldisilazan 99%	LEVEL 6 480 min	999-97-3 Hexamethyldisilazan 99%	LEVEL 6 480 min	999-97-3 Hexamethyldisilazan 99%	Not Tested
Mixed Solution Hydranal® -Composite 2	LEVEL 6 480 min	Mixed Solution Hydranal® -Composite 2	LEVEL 6 480 min	Mixed Solution Hydranal® -Composite 2	LEVEL 6 480 min
7803-57-8 Hydrazine monohydrate 80%	LEVEL 6 480 min	7803-57-8 Hydrazine monohydrate 80%	LEVEL 5 430 min	7803-57-8 Hydrazine monohydrate 80%	Not Tested
7803-57-8 Hydrazine monohydrate 98%	LEVEL 6 480 min	7803-57-8 Hydrazine monohydrate 98%	LEVEL 4 180 min	7803-57-8 Hydrazine monohydrate 98%	LEVEL 4 150 min
7647-01-0 Hydrochloric Acid 37%	LEVEL 6 480 min	7647-01-0 Hydrochloric Acid 37%	LEVEL 4 130 min	7647-01-0 Hydrochloric Acid 37%	LEVEL 3 98 min
7664-39-3 Hydrofluoric Acid 40%	Not Tested	7664-39-3 Hydrofluoric Acid 40%	LEVEL 1 12 min	7664-39-3 Hydrofluoric Acid 40%	LEVEL 0 8 min
7664-39-3 Hydrofluoric Acid 48%	LEVEL 4 168 min	7664-39-3 Hydrofluoric Acid 48%	LEVEL 0 5 min	7664-39-3 Hydrofluoric Acid 48%	LEVEL 0 0 min
7664-39-3 Hydrofluoric Acid 60%	LEVEL 2 42 min	7664-39-3 Hydrofluoric Acid 60%	Not Tested	7664-39-3 Hydrofluoric Acid 60%	Not Tested

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

7664-39-3 Hydrogen Fluoride 48%	LEVEL 4 168 min	7664-39-3 Hydrogen Fluoride 48%	LEVEL 0 5 min	7664-39-3 Hydrogen Fluoride 48%	Not Tested
7722-84-1 Hydrogen Peroxide 30%	LEVEL 6 480 min DR -9%	7722-84-1 Hydrogen Peroxide 30%	LEVEL 6 480 min	7722-84-1 Hydrogen Peroxide 30%	LEVEL 6 480 min
7722-84-1 Hydrogen Peroxide 12%	LEVEL 6 480 min	7722-84-1 Hydrogen Peroxide 12%	LEVEL 6 480 min	7722-84-1 Hydrogen Peroxide 12%	Not Tested
78-83-1 Isobutanol 99%	LEVEL 6 480 min	78-83-1 Isobutanol 99%	LEVEL 3 76 min	78-83-1 Isobutanol 99%	LEVEL 2 39 min
540-84-1 Iso-Octane 99%	LEVEL 6 480 min	540-84-1 Iso-Octane 99%	LEVEL 6 480 min	540-84-1 Iso-Octane 99%	Not Tested
4098-71-9 Isophorone diisocyanate 100%	LEVEL 6 480 min	4098-71-9 Isophorone diisocyanate 100%	Not Tested	4098-71-9 Isophorone diisocyanate 100%	Not Tested
67-63-0 Isopropanol 100%	Not Tested	67-63-0 Isopropanol 100%	LEVEL 2 46 min	67-63-0 Isopropanol 100%	LEVEL 2 33 min
67-63-0 Isopropanol 70%	LEVEL 6 480 min	67-63-0 Isopropanol 70%	LEVEL 3 70 min	67-63-0 Isopropanol 70%	LEVEL 2 58 min
Mixed Solution LiPF6	LEVEL 6 480 min	Mixed Solution LiPF6	LEVEL 6 480 min	Mixed Solution LiPF6	Not Tested
7550-35-8 Lithium bromide 30%	LEVEL 6 480 min DR -1%	7550-35-8 Lithium bromide 30%	LEVEL 6 480 min DR 22%	7550-35-8 Lithium bromide 30%	Not Tested
108-39-4 m-Cresol 98.5%	LEVEL 4 212 min	108-39-4 m-Cresol 98.5%	LEVEL 2 57 min	108-39-4 m-Cresol 98.5%	Not Tested
60-24-2 2-Mercaptoethanol 99%	LEVEL 3 63 min	60-24-2 2-Mercaptoethanol 99%	LEVEL 0 1 min	60-24-2 2-Mercaptoethanol 99%	LEVEL 0 1 min
67-56-1 Methanol 99,9%	LEVEL 2 54 min	67-56-1 Methanol 99,9%	LEVEL 0 5 min	67-56-1 Methanol 99,9%	LEVEL 0 0 min
67-56-1 Methanol, 20%	Not Tested	67-56-1 Methanol, 20%	Not Tested	67-56-1 Methanol, 20%	LEVEL 3 65 min
109-86-4 Methoxyethanol	LEVEL 2 49 min	109-86-4 Methoxyethanol	Not Tested	109-86-4 Methoxyethanol	Not Tested

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

107-98-2 1-Methoxy-2-propanol 99%	LEVEL 3 72 min	107-98-2 1-Methoxy-2-propanol 99%	Not Tested	107-98-2 1-Methoxy-2-propanol 99%	Not Tested
5332-73-0 3-Methoxypropylamine 99%	LEVEL 0 7 min	5332-73-0 3-Methoxypropylamine 99%	Not Tested	5332-73-0 3-Methoxypropylamine 99%	Not Tested
37143-54-7 1-Methoxy-2-propylamine 95%	LEVEL 1 12 min	37143-54-7 1-Methoxy-2-propylamine 95%	LEVEL 0 3 min	37143-54-7 1-Methoxy-2-propylamine 95%	Not Tested
108-87-2 Methylcyclohexane 99,9%	LEVEL 2 58 min	108-87-2 Methylcyclohexane 99,9%	LEVEL 2 55 min	108-87-2 Methylcyclohexane 99,9%	LEVEL 2 55 min
78-93-3 Methyl ethyl ketone 99%	LEVEL 0 2 min	78-93-3 Methyl ethyl ketone 99%	Not Tested	78-93-3 Methyl ethyl ketone 99%	Not Tested
108-10-1 Methyl Isobutyl Ketone 99%	LEVEL 0 8 min	108-10-1 Methyl Isobutyl Ketone 99%	LEVEL 0 1 min	108-10-1 Methyl Isobutyl Ketone 99%	Not Tested
80-62-6 Methyl Methacrylate 99%	LEVEL 0 8 min	80-62-6 Methyl Methacrylate 99%	LEVEL 0 2 min	80-62-6 Methyl Methacrylate 99%	Not Tested
75-65-0 2-methyl-2-propanol 99.5%	LEVEL 6 480 min DR 32%	75-65-0 2-methyl-2-propanol 99.5%	Not Tested	75-65-0 2-methyl-2-propanol 99.5%	Not Tested
1634-04-4 Methyl Tert Butyl Esther (MTBE)	LEVEL 1 14 min	1634-04-4 Methyl Tert Butyl Esther (MTBE)	LEVEL 1 11 min	1634-04-4 Methyl Tert Butyl Esther (MTBE)	Not Tested
96-47-9 2-Methyltetrahydrofuran 99,9%	LEVEL 0 4 min	96-47-9 2-Methyltetrahydrofuran 99,9%	LEVEL 0 1 min	96-47-9 2-Methyltetrahydrofuran 99,9%	Not Tested
Mixed Solution Mucocit®-T branded mixture	LEVEL 6 480 min	Mixed Solution Mucocit®-T branded mixture	LEVEL 6 480 min	Mixed Solution Mucocit®-T branded mixture	LEVEL 6 480 min
124-18-5 n-Decane	Not Tested	124-18-5 n-Decane	Not Tested	124-18-5 n-Decane	LEVEL 2 58 min
Mixed Solution Neopredisan 135-1	Not Tested	Mixed Solution Neopredisan 135-1	LEVEL 1 20 min	Mixed Solution Neopredisan 135-1	Not Tested
142-82-5 n-Heptane 99%	LEVEL 2 56 min	142-82-5 n-Heptane 99%	LEVEL 3 91 min	142-82-5 n-Heptane 99%	LEVEL 2 41 min DR 48%
110-54-3 n-Hexane 95%	LEVEL 4 138 min	110-54-3 n-Hexane 95%	LEVEL 3 97 min	110-54-3 n-Hexane 95%	LEVEL 1 28 min

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

54-11-5 Nicotine 98%	Not Tested	54-11-5 Nicotine 98%	LEVEL 4 151 min	54-11-5 Nicotine 98%	Not Tested
7697-37-2 Nitric Acid, 50%	Not Tested	7697-37-2 Nitric Acid, 50%	LEVEL 2 54 min	7697-37-2 Nitric Acid, 50%	Not Tested
7697-37-2 Nitric Acid 70%	LEVEL 4 122 min	7697-37-2 Nitric Acid 70%	LEVEL 0 5 min	7697-37-2 Nitric Acid 70%	LEVEL 0 4 min
7697-37-2 Nitric acid 99%	LEVEL 0 2 min	7697-37-2 Nitric acid 99%	Not Tested	7697-37-2 Nitric acid 99%	Not Tested
872-50-4 N-methyl-2-pyrrolidone	LEVEL 2 43 min	872-50-4 N-methyl-2-pyrrolidone	LEVEL 2 32 min	872-50-4 N-methyl-2-pyrrolidone	Not Tested
109-66-0 n-Pentane 98%	LEVEL 2 45 min	109-66-0 n-Pentane 98%	LEVEL 2 56 min	109-66-0 n-Pentane 98%	Not Tested
71-23-8 n-Propanol 99,5%	LEVEL 5 304 min	71-23-8 n-Propanol 99,5%	Not Tested	71-23-8 n-Propanol 99,5%	Not Tested
71-23-8 n-Propanol	Not Tested	71-23-8 n-Propanol	LEVEL 2 46 min	71-23-8 n-Propanol	Not Tested
95-54-4 o-Phenylenediamine	Not Tested	95-54-4 o-Phenylenediamine	LEVEL 5 308 min	95-54-4 o-Phenylenediamine	Not Tested
79-37-8 Oxalyl chloride	LEVEL 0 1 min	79-37-8 Oxalyl chloride	Not Tested	79-37-8 Oxalyl chloride	Not Tested
7601-90-3 Perchloric acid 70%	LEVEL 6 480 min	7601-90-3 Perchloric acid 70%	Not Tested	7601-90-3 Perchloric acid 70%	Not Tested
64742-49-0 Petroleum benzene 80-100°C	LEVEL 6 480 min	64742-49-0 Petroleum benzene 80-100°C	LEVEL 6 480 min	64742-49-0 Petroleum benzene 80-100°C	LEVEL 6 480 min
108-95-2 Phenol 50%	LEVEL 4 163 min	108-95-2 Phenol 50%	LEVEL 1 23 min	108-95-2 Phenol 50%	LEVEL 1 15 min
108-95-2 Phenol 85%	LEVEL 4 138 min	108-95-2 Phenol 85%	Not Tested	108-95-2 Phenol 85%	Not Tested
108-95-2 Phenol 4%	Not Tested	108-95-2 Phenol 4%	LEVEL 1 22 min	108-95-2 Phenol 4%	Not Tested

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

108-95-2 Phenol aqueous solution 0.45%	Not Tested	108-95-2 Phenol aqueous solution 0.45%	LEVEL 6 480 min DR 35%	108-95-2 Phenol aqueous solution 0.45%	Not Tested
Mixed Solution Phenol:Chloroform Isoamyl Alcohol 25:24:1	LEVEL 0 9 min	Mixed Solution Phenol:Chloroform Isoamyl Alcohol 25:24:1	LEVEL 0 1 min	Mixed Solution Phenol:Chloroform Isoamyl Alcohol 25:24:1	Not Tested
108-95-2 Phenol 0.1% solution	LEVEL 6 480 min	108-95-2 Phenol 0.1% solution	LEVEL 6 480 min	108-95-2 Phenol 0.1% solution	LEVEL 6 480 min
7664-38-2 Phosphoric Acid, 30%	LEVEL 6 480 min	7664-38-2 Phosphoric Acid, 30%	LEVEL 6 480 min	7664-38-2 Phosphoric Acid, 30%	LEVEL 6 480 min
7664-38-2 Phosphoric acid, 85%	LEVEL 6 480 min	7664-38-2 Phosphoric acid, 85%	LEVEL 6 480 min	7664-38-2 Phosphoric acid, 85%	Not Tested
3761-53-3 Ponceau 2R	LEVEL 6 480 min	3761-53-3 Ponceau 2R	LEVEL 6 480 min	3761-53-3 Ponceau 2R	Not Tested
6226-79-5 Ponceau S	LEVEL 6 480 min	6226-79-5 Ponceau S	LEVEL 6 480 min	6226-79-5 Ponceau S	Not Tested
1310-58-3 Potassium Hydroxide 40%	LEVEL 6 480 min	1310-58-3 Potassium Hydroxide 40%	LEVEL 6 480 min	1310-58-3 Potassium Hydroxide 40%	LEVEL 6 480 min
123-38-6 Propionaldehyde, 97%	LEVEL 0 2 min	123-38-6 Propionaldehyde, 97%	LEVEL 0 2 min	123-38-6 Propionaldehyde, 97%	Not Tested
75-56-9 Propylene oxide 99%	LEVEL 0 2 min	75-56-9 Propylene oxide 99%	LEVEL 0 0 min	75-56-9 Propylene oxide 99%	LEVEL 0 0 min
110-86-1 Pyridine	LEVEL 0 6 min	110-86-1 Pyridine	LEVEL 0 1 min	110-86-1 Pyridine	LEVEL 0 0 min
598-75-4 Secondary isoamyl alcohol 98%	LEVEL 6 480 min	598-75-4 Secondary isoamyl alcohol 98%	LEVEL 2 55 min	598-75-4 Secondary isoamyl alcohol 98%	LEVEL 2 30 min
127-09-3 Sodium acetate Sat. solution	LEVEL 6 480 min	127-09-3 Sodium acetate Sat. solution	LEVEL 6 480 min	127-09-3 Sodium acetate Sat. solution	LEVEL 6 480 min
1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min	1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min	1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min DR 10%
1310-73-2 Sodium Hydroxide, 50%	LEVEL 6 480 min	1310-73-2 Sodium Hydroxide, 50%	LEVEL 6 480 min	1310-73-2 Sodium Hydroxide, 50%	LEVEL 6 480 min

SHIELDskin CHEM* NEO NITRILE* 300

SHIELDskin* ORANGE NITRILE* 260

ecoSHIELD* Eco Nitrile PF 250

7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min	7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min	7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min
100-42-5 Styrene 99.9%	LEVEL 0 5 min	100-42-5 Styrene 99.9%	LEVEL 0 0 min	100-42-5 Styrene 99.9%	LEVEL 0 0 min
7664-93-9 Sulphuric Acid 10%	LEVEL 6 480 min	7664-93-9 Sulphuric Acid 10%	LEVEL 6 480 min	7664-93-9 Sulphuric Acid 10%	LEVEL 6 480 min
7664-93-9 Sulphuric acid 95%-98%	LEVEL 2 57 min	7664-93-9 Sulphuric acid 95%-98%	LEVEL 0 8 min	7664-93-9 Sulphuric acid 95%-98%	LEVEL 0 0 min
7664-93-9 Sulphuric acid 50%	LEVEL 6 480 min	7664-93-9 Sulphuric acid 50%	LEVEL 6 480 min	7664-93-9 Sulphuric acid 50%	LEVEL 6 480 min
Mixed Solution Terralin protect	Not Tested	Mixed Solution Terralin protect	LEVEL 3 103 min	Mixed Solution Terralin protect	LEVEL 1 13 min
127-18-4 Tetrachloroethylene 99%	LEVEL 1 10 min	127-18-4 Tetrachloroethylene 99%	LEVEL 0 5 min	127-18-4 Tetrachloroethylene 99%	Not Tested
109-99-9 Tetrahydrofuran 99.9%	LEVEL 0 1 min	109-99-9 Tetrahydrofuran 99.9%	LEVEL 0 0 min	109-99-9 Tetrahydrofuran 99.9%	LEVEL 0 0 min
75-59-2 Tetramethylammonium hydroxide 2.5%	LEVEL 6 480 min	75-59-2 Tetramethylammonium hydroxide 2.5%	LEVEL 6 480 min	75-59-2 Tetramethylammonium hydroxide 2.5%	LEVEL 6 480 min
108-88-3 Toluene 99,9%	LEVEL 0 4 min	108-88-3 Toluene 99,9%	LEVEL 0 1 min	108-88-3 Toluene 99,9%	Not Tested
584-84-9 Toluene diisocyanate 95%	LEVEL 0 0 min	584-84-9 Toluene diisocyanate 95%	LEVEL 0 0 min	584-84-9 Toluene diisocyanate 95%	LEVEL 0 0 min
76-03-9 Trichloroacetic acid 10%	LEVEL 6 480 min	76-03-9 Trichloroacetic acid 10%	LEVEL 6 480 min	76-03-9 Trichloroacetic acid 10%	Not Tested
121-44-8 Triethylamine 99%	LEVEL 2 37 min	121-44-8 Triethylamine 99%	LEVEL 1 23 min	121-44-8 Triethylamine 99%	Not Tested
76-05-1 Trifluoroacetic acid 99%	LEVEL 2 57 min	76-05-1 Trifluoroacetic acid 99%	LEVEL 0 1 min	76-05-1 Trifluoroacetic acid 99%	LEVEL 0 0 min
95-63-6 1,2,4- Trimethylbenzene 98%	LEVEL 1 21 min	95-63-6 1,2,4- Trimethylbenzene 98%	LEVEL 1 13 min	95-63-6 1,2,4- Trimethylbenzene 98%	Not Tested

SHIELDskin CHEM* NEO NITRILE* 300**SHIELDskin* ORANGE NITRILE* 260****ecoSHIELD* Eco Nitrile PF 250**

108-67-8 1,3,5-Trimethylbenzene 98%	LEVEL 1 19 min	108-67-8 1,3,5-Trimethylbenzene 98%	LEVEL 1 10 min	108-67-8 1,3,5-Trimethylbenzene 98%	Not Tested
77-86-1 Tris (hydroxymethyl) aminomethane Sat. solution	LEVEL 6 480 min	77-86-1 Tris (hydroxymethyl) aminomethane Sat. solution	LEVEL 6 480 min	77-86-1 Tris (hydroxymethyl) aminomethane Sat. solution	LEVEL 6 480 min
72-57-1 Trypan blue	LEVEL 6 480 min	72-57-1 Trypan blue	LEVEL 6 480 min	72-57-1 Trypan blue	Not Tested
1330-20-7 Xylene 98,5%	LEVEL 0 8 min	1330-20-7 Xylene 98,5%	LEVEL 0 4 min	1330-20-7 Xylene 98,5%	LEVEL 0 2 min

