



**TYPICAL ANALYSIS REPORT OF 10% PD/C  
CATALYST (50% wet basis)**

Elements	
Carrier Material	Activated Carbon Powder
Total Surface Area(BET)	950 m <sup>2</sup> /g
Total Pore Volume	1.0 cm <sup>3</sup> /g
Bulk Density	250 Kg /m <sup>3</sup>
pH	8.5 – 9.5
Moisure Content	50.50%
Min Assay(Pd Content on Dry basis)	9.90- 10.00%