



**TYPICAL ANALYSIS REPORT OF 20% PALLADIUM
HYDROXIDE ON CARBON – Wet Basis**

Elements	
Carrier Material	Activated Carbon Powder
Total Surface Area(BET)	950 m ² /g
Total Pore Volume	1.0 cm ³ /g
Bulk Density	250 Kg /m ³
pH	9 – 10
Moisure Content	8 -12%
Min Assay(Pd Content on Dry basis)	19.50- 20.00%