



Plating Limit For Cyanideless 24KT Gold Plating Solution

CLYGPS is a ready-to-use plating bath at the concentration of 2 g/l of gold. No preparation is required.

The initial gold concentration; for example, with a bath operating at a concentration of 2 g / l it can be used upto a maximum consumption of **0.4 g / l** of Gold.

| Deposit Data | |
|------------------------------|--------------|
| Purity (%) | 99,9 |
| Hardness [HV 0.01] | 160 - 220 |
| Density [g/cm ³] | 19 |
| Thickness from-to [μm] | 0.02 – 0.20 |
| Aspect | Shiny |
| Color | 24 KT Yellow |