



Plating Limit For Palladium Bath Plating Solution

PBPS is a ready-to-use plating bath at the concentration of 2 g/l of palladium. No preparation is required.

The initial palladium concentration; for example, with a bath operating at a concentration of 2 g / l it can be used upto a maximum consumption of **0.4 g / l** of palladium.

Deposit Data	
Purity (%)	99,9
Hardness [HV 0.01]	165 - 225
Density [g/cm ³]	12
Thickness from-to [μm]	0.02 – 0.20
Aspect	Shiny
Color	Bright White