

REFINE LEATHER



691 / STON / STONE

REFINE – ANILINE LEATHER

GRAIN LEATHER FROM EUROPEAN RAW HIDES. THE LEATHER IS DYED THROUGH, CHROME TANNED AND PRODUCED WITHOUT THE USE OF PCP AND CFC WHICH CAN BE DAMAGING TO THE ENVIRONMENT.

THICKNESS (MM)	1,0-1,2
FLEXING ENDURANCE	≥30.000 (IUP 20 / EN ISO 5402)
LIGHTFASTNESS (SCALE 1-8)	3 (EN ISO 105-B02)
RUBBING, DRY, 100 RUBBINGS (SCALE 1-5)	≥3 (IUF 450 / EN ISO 11640)
RUBBING, WET, 20 RUBBINGS (SCALE 1-5)	≥3 (IUF 450 / EN ISO 11640)
RUBBING, SWEAT, 20 RUBBINGS (SCALE 1-5)	≥3 (IUF 450 / EN ISO 11640)
TEAR STRENGTH (N)	≥20 (IUP 40 / EN ISO 3377-1)
FIRE TEST	BS5852- PART 1, CAL TB 117, EN 1021-1&2

REFINE LEATHER




550 / YELW / YELLOW



565 / ONGE / ORANGE




4009 / RED / RED




692 / LGRN / LIGHT GREEN



778 / TRKS / TURKIS



779 / SBLE / SEA BLUE



681 / DKGR / DARK GREEN



7008 / PURP / PURPLE



BEIG / BEIGE



197 / CREM / CREAM



691 / STON / STONE



258 / NOUG / NOUGAT



551 / WSKY / WHISKY




250 / COGN / COGNAC



229 / CHUT / CHESTNUT



240 / COPP / COPPER



4060 / FUSC / FUCHSIA



329 / DKBW / DARK BROWN



854 / LIGY / LIGHT GREY



855 / GREY / GREY



842 / BLCK / BLACK

REFINE LEATHER