

Test Report

No. 2026034/SD

Date: Jan 05 2005

Page 1 of 2

TEC - HUB ASIA LTD. UNIT 2021, METROPOLE SQUARE, 2 ON YIU STREET, SHATIN, N.T., HONG KONG

The following sample(s) was/were submitted by/ on behalf of the client as:

Sample Description

: 1. STATIC INTERCEPT BAG (CLEAN IRON METAL SHEET)

2. STATIC INTERCEPT BAG (FRESH SILVER COATED PCB)

3. CORROSION INTERCEPT BAG (CLEAN COPPER SHEET)

SGS Job No.

1676113

Quantity Submitted

5 PCS.

Sample Receiving Date Test Performing Date

: DEC 21, 2004 AND DEC 29, 2004

: DEC 21, 2004 TO JAN 05, 2005

Test Requested

: Salt Spray (Fog) Test (ASTM B117-03)

Test Result

: Details, please refer to the following page(s).

*** SAMPLE RETURNED ***

Signed for and on behalf of SGS Hong Kong Ltd.

Siu Hok Wai, Jaffee Section Mahager

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company.

Member of the SGS Group (SGS SA)



Test Report

No. 2026034/SD

Date: Jan 05 2005

Page 2 of 2

Salt Spray (Fog) Test (ASTM B117-03)

Scope

To evaluate the corrosion resistance of metals and coated metals.

No. of Specimens

3 pcs.

NaCl Solution

5 % sodium chloride dissolve in 95 % distill water.

Test Machine

Salt Spray Tester.

Test Duration

168 hours. (As per client requirement)

Test Temperature

35+2 deg. C

Test Results

Specimen	Observation
A	6
В	6
С	6

Sample Descriptions:

- Fresh Silver coated PCB packed into a static intercept bag with thickness 3 mil.
- Clean Copper sheet packed into a corrosion intercept bag with thickness 3 mil.
- Clean Iron Metal Sheet packed into a static intercept bag with thickness 3 mil.

Observation Rating

- : 6 Completely free of corrosion.
 - 5 Very minor deterioration in one location.
 - 4 Minor deterioration in several areas.
 - 3 Scattered deterioration.
 - 2 More extensive deterioration.
 - 1 Severe deterioration in many locations.

Note

: ASTM B117 does not specify the type of test specimen or exposure periods to be used for a specific product, nor the interpretation to be given to the results.

Remarks

- : 1. All the tested samples were returned to client.
 - 2. Photo Appendix included.

*** End of Report ***

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company.



2026034/SD

Sample Receiving Date :

DEC 21, 2004

PHOTO APPENDIX



Sample C (After Test) SGS authenticate the photo on original report only

Page 1 of 5

Authorized Signature



2026034/SD

Sample Receiving Date: DEC 21, 2004

PHOTO APPENDIX



Sample B (After Test) SGS authenticate the photo on original report only

Page 2 of 5

Authorized Signature



2026034/SD

Sample Receiving Date:

DEC 21, 2004

PHOTO APPENDIX



Sample A (After Test) SGS authenticate the photo on original report only

Page 3 of 5

Authorized Signature



2026034/SD

Sample Receiving Date:

DEC 21, 2004

PHOTO APPENDIX



Sample C, B (Before Test) SGS authenticate the photo on original report only

Page 4 of 5


Authorized Signature



2026034/SD

Sample Receiving Date: DEC 21, 2004

PHOTO APPENDIX



Sample A (Before Test) SGS authenticate the photo on original report only

Page 5 of 5

Authorized Signature