



## All Purpose Acrylic Primer/Undercoat

### Data Sheet

#### Description:

A Premium quality Primer designed specifically for exterior surfaces such as Timber, masonry and fibre-cement board. It may be overcoated with most exterior acrylic topcoats where it will extend the life of the system. It may also be used interior on timber and masonry surfaces.

#### Benefits:

Can be used on a wide range of exterior and interior substrates. Very good coverage with excellent hiding power giving a smooth finish for subsequent topcoats. Easy wash-up with water, Can be applied by Brush, Roller or Spray.

#### Physical Properties

<b>Resin Type:</b>	Hybrid Acrylic emulsion
<b>Solvent:</b>	Water
<b>Colour:</b>	White, may be tinted
<b>Finish:</b>	Eggshell
<b>Drying time:</b>	1 hours @ 18°C
<b>Recoat time:</b>	2 hours @ 18°C
<b>Dry Film Thickness:</b>	50µ minimum
<b>No. of coats:</b>	1 - 2
<b>Theoretical Coverage:</b>	6-7m <sup>2</sup> per litre to attain 50µ DF.
<b>Primer Needed:</b>	None
<b>Thinning &amp; Cleaning:</b>	Thin only to suit application method. Water cleanup.

#### Performance:

- Good adhesion to solid plaster, wood , concrete and many other substrates used in the building industry.
- Fast drying and re-coat times
- Good hold out for following finish coats.
- Recommended primer/undercoat for general exterior areas.
- **All Purpose Acrylic Primer/Undercoat** can be used under solvent enamel finishes.
- May be tinted to light and mid-tone colours.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Paint Tech makes no representation as to the completeness and accuracy thereof. In no event will Paint Tech be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.

**Limitations:**

- Do not apply when temperature is below or expected to fall under 10°C.
- Light sand required before application of finishing coats if left for more than 7 days.
- Test area recommended for normal hard to prime surfaces.

**Substrate Preparation:**

All surfaces must be free from loose or flaking paint, dust, oil and grease etc. If mould and fungus is present use **Paint Tech Moss and Mould Kill**. Water blasting at 3000psi is the recommended method of surface preparation. New timber surfaces should be sanded smooth and dusted prior to application. Fill all nail holes, imperfections and cracks with suitable filler.

**Application:**

All Purpose Acrylic Primer Undercoat may be applied by brush roller or spray. Thinning with water is only recommended for spray application.

Although the information and recommendations set down here in this document are presented in good faith and believed to be correct, Paint Tech makes no representation as to the completeness and accuracy thereof. In no event will Paint Tech be responsible for damages of any nature what so ever resulting from the use or reliance upon this information. No representations or warranties expressed or implied or merchantability, fitness for purpose or any other nature are made hereunder with respect to information or the product to which the information or Technical Data Sheet refers.