

Novepoxy Application Tips

March 2023

- All paint tools to be paint free e.g. new drill, sleeves, brush, tray.
- When painting a floor it is always best that at least two people apply the coating. 1 to cut in and 1 to roll or spray.
- Air movement is very important when the product is drying. Fans, doors, or have windows open. You don't want a massive breeze, just air movement.
- High levels of humidity will affect the drying and sheen of the product.
- Unless experienced with two pot products it is best not to alter the pack size. This product is a 3:1 ratio. Adding more part B will NOT make it cure faster. It will just make it sticky.
- For floors we recommend a ½” roller sleeve. Foam rollers are good if doing cabinets, benches.
- Colours will appear lighter when wet or just applied.
- Concrete floors that have a rougher surface profile could use more product and might require to be left longer for recoat times. This is dependent on ambient atmosphere temperature and humidity levels.
- Part A must be mixed first to ensure even colour dispersion. Then both pack contents must be mixed together to ensure even mixing drill mix on low for at least 2 mins or hand mix with a clean flat stick. Do not mix too vigorously as the product will become aerated.
- Once the part A and part B have been mixed leave for 10-15 minutes to allow the product to fully infuse and for bubbles to dissipate.
- All paint gear should be washed immediately in warm soapy water. Do not leave submerged in water without washing.
- Concrete floor profile for painting should have a 150-180 grit for adhesion.
- Clear Novepoxy is not recommended over white colours.
- I like to apply 1st coat day 1, 2nd coat day 2, don't walk on it day 3, and by day 4 it will be all good.

Please call if you want to ask any questions. We are happy to help.

You are putting down a floor that will likely last you 25 years so there is no rush.

You will never regret an epoxy floor!